

PRODUCT DATA SHEET

Sika® Backer Rod Fire

Backing rod for fire resistant joint sealing

DESCRIPTION

Sika® Backer Rod Fire is a circular, compressible, mineral wool based backing rod wrapped with a glass fibre yarn.

USES

Sika® Backer Rod Fire may only be used by experienced professionals.

- Designed as a backing rod for fire resistant joint sealing in horizontal and vertical building structure applications
- Applied in conjunction with Sikaflex® PRO-3, SikaHyflex®-250 Facade or Sikaflex® AT Connection

CHARACTERISTICS / ADVANTAGES

- Easy to apply
- Adapts to joint width and alignment irregularities
- Helps to regulate the sealant profile

APPROVALS / CERTIFICATES

- CE marking and Declaration to Performance to European Technical Assessment ETA 17/0980 based on EAD 350141-00-1106:2017 – Fire stopping and fire sealing products, linear joint and gap seal
- Resistance to fire classification EN 13501-2, Warringtonfire, Report No. 405212
- Reaction to fire classification, EN 13501-1, Exova Warringtonfire, Report No. 391173

PRODUCT INFORMATION

Mineral fibre wool wrapped in a glass fibre yarn		
Diameter	Roll length	
12 mm*	50 m	
15 mm	50 m	
20 mm	30 m	
30 mm	30 m	
40 mm	30 m	
50 mm	25 m	
60 mm	25 m	
* Not on stock in DK		
Circular profile		
72 months from the date of production		
	Diameter 12 mm* 15 mm 20 mm 30 mm 40 mm 50 mm 60 mm * Not on stock in DK Circular profile	Diameter Roll length 12 mm* 50 m 15 mm 50 m 20 mm 30 m 30 mm 30 m 40 mm 30 m 50 mm 25 m 60 mm 25 m * Not on stock in DK Circular profile

PRODUCT DATA SHEET Sika® Backer Rod Fire

May 2021, Version 03.01 020515100000000000

Storage conditions	·	ed in original, unopened and undamaged pack- temperatures between -20 °C and +70 °C. Always		
Density	~250 kg/m³	(EN 1602)		
Dimensions	Note: Reference must be made to limitations regarding dimensions and configuration described in the EN 13501-2 classification report and / or ETA 17/0980 Sika® Backer Rod Fire must be installed at a minimum compression rate of 15 %. Select the correct diameter using the following table:			
	Joint width	Diameter		
	7–10,2 mm	12mm		
	9– 12,7 mm	15 mm		
	12–17mm	20 mm		
	16–25,5 mm	30 mm		
	24–34 mm	40 mm		
	32–42,5 mm	50 mm		
	40–51 mm	60 mm		

TECHNICAL INFORMATION

Reaction to fire	A1	(EN 135	01-1)
------------------	----	---------	-------

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER INFORMATION

- EN 13501-2 classification report
- ETA 17/0980
- Sika Method Statement: Sika® Backer Rod Fire
- Sika passive fire protection handbook

ECOLOGY, HEALTH AND SAFETY

REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in this product data sheet.Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0.1 % (w/w)

APPLICATION INSTRUCTIONS

APPLICATION METHOD / TOOLS

Strictly follow installation procedures as defined in method statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

Important: The ends of adjoining rods and at detailing locations such as corners must be in tight contact with each other to maintain maximum fire resistance.

- 1. Place the oversized Sika® Backer Rod Fire into the joint and push with a blunt tool to tightly fit against the joint sides at the required depth.
- Seal the joint with Sikaflex® PRO-3, SikaHyflex®-250
 Facade or Sikaflex® AT Connection. Refer to individual Product Data Sheets.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.



LEGAL NOTES

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

Sika Danmark A/S

Hirsemarken 5 3520 Farum Tlf. +45 48 18 85 85 www.sika.dk







PRODUCT DATA SHEET Sika® Backer Rod Fire May 2021, Version 03.01 0205151000000000003 SikaBackerRodFire-en-DK-(05-2021)-3-1.pdf

