

Test report

SikaForce®-7720 L105

Sika Services AG
Tueffenwies 16
CH-8048 Zurich
Switzerland

File: PFB10014a
Serial No.: 13226
Ref.: BP/DB
Encl.: 1

Date: 2011-12-01

Danish Institute of Fire and Security Technology

Jernholmen 12, DK-2650 Hvidovre
Phone: +45 36 34 90 00, Fax: +45 36 34 90 01
E-mail: dbi@dbi-net.dk
www.dbi-net.dk

The results relate only to the items tested.
The test report should only be reproduced in extenso
- in extracts only with a written agreement with
this institute.



1 SPONSOR

Sika Services AG
Tueffenwies 16
CH-8048 Zurich
Switzerland

2 PRODUCT

Two component adhesive designated SikaForce®-7720 L105.

3 NAME OF MANUFACTURER

The sponsor is the manufacturer.

4 TEST METHOD

The test specimens have been subjected to the standard fire test complying with the International Code for Application of Fire Test Procedures, 2010 Resolution MSC.307(88), 2010 FTP Code, Annex 1 Part 5: "Test for surface flammability" in effect on 1 July 2012.

5 SAMPLE

Sampling

The sampling was done by the sponsor.

On 2011-11-01 DBI-Danish Institute of Fire and Security Technology received the following samples:

One can of SikaForce®-7720 L105 (approx. 1.6 kg) and one can of SikaForce®-7050 (approx. 1.0 kg).

DBI mixed the two components in a 100/19 ratio (weight) and applied 250 g/m² of (wet) adhesive in one layer onto the surface of 5 pieces of non-combustible calcium silicate board each with dimensions 795 x 153 x 10 mm and density 800 ± 100 kg/m³, cf. paragraph 4.11 of appendix 4 to part 5.

Material specification (stated by the sponsor)

Non-sagging assembly adhesive.

Component A: SikaForce®-7720 L105. Component B: SikaForce®-7050 (hardener)

Recommended amount for use: approx. 250 g/m² (wet adhesive).

Further material specification was given by the sponsor and has been filed at DBI under the file number below.

6 CONDITIONING

The specimens were conditioned in accordance with paragraph 7.7 of appendix 1 to part 5.

7 TEST RESULTS

Date of test: 2011-11-28.

Pilot flame: Impinging.

The test results are shown in full detail in enclosure 1.

Derived fire characteristics

Test No.	1	2	3	Average
Duration of test (s)	257	261	274	-
CFE (kW/m ²)	38.2	34.3	37.0	36.5
Q _{sb} (MJ/m ²)	2.2	1.9	1.9	2.0
Q _t (MJ)	0	0	0	0
q _p (kW)	1.6	1.1	1.9	1.5
Burning droplets No.	0	0	0	-

Observations: None

CFE: Critical flux at extinguishment

Q_{sb}: Heat for sustained burning

Q_t: Total heat release

q_p: Peak heat release rate

8 CONCLUSION

The investigated sample of SikaForce® - 7720 L105 (250 g/m² wet), applied onto calcium silicate board, fulfils the surface flammability criteria for linings and ceilings as listed in IMO FTPC Part 5 and is therefore considered to meet the requirement for low flame-spread in compliance with the relevant regulations in chapter II - 2 of the Convention.



9 VALIDITY OF THE TEST RESULT IN RELATION TO THE PREVIOUS FTP CODE*

Reference is made to the *International Code for Application of Fire Test Procedures, Resolution MSC.61(67), FTP Code, Annex 1 Part 5 "Test for surface flammability", together with the unified interpretations of SOLAS chapter II-2, the FSS Code, the FTP Code and related fire test procedures (IMO MSC/Circ. 1120).

Whilst the test was conducted to the International Code for Application of Fire Test Procedures, 2010 Resolution MSC.307(88), 2010 FTP Code, Annex 1 Part 5 "Test for surface flammability", it is our opinion when the test results described in this report are assessed in compliance of Resolution MSC.61(67) Annex 1 Part 5 "Test for surface flammability", the product may be regarded as having low flame-spread characteristics.

Furthermore, it is our opinion that the test is in compliance with the requirements of:

- Russian Maritime Register of Shipping, St. Petersburg, cf. Recognition Certificate of Testing Laboratory No. 10-02059.009 valid until September 18, 2015.

Note

The test results relate only to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Dan Bluhme
Senior Advisor M.Sc. Civ.Eng

/

Bjørn Petersen
Laboratory Technician

Sika Services AG
Tueffenwies 16
CH-8048 Zurich
Switzerland



FIRE TEST PROCEDURES FOR SURFACE FLAMMABILITY OF BULKHEAD, CEILING, DECK FINISH MATERIALS AND PRIMARY DECK COVERINGS

Sponsor: Sika Services AG Date of test: 2011-11-28
Product: SikaForce® - 7720 L105 with hardener SikaForce®-7050
Applied amount: 250 g/m² Pilot flame: Impinging

Test results

Test 1:	Time to ignition :	8 s
	Time to flameout :	77 s
	Extent of burn (mm) :	245
	Critical flux at extinguishment (kW/m ²) :	38.24
	Heat for ignition (MJ/m ²) :	2.015
	Average heat for sustained burning (MJ/m ²) :	2.209
	Peak heat release rate (kW) :	1.63
	Time to peak heat release rate :	48 s
	Total heat release (MJ) :	0.041
	Burning droplets :	None
Test 2:	Time to ignition :	6 s
	Time to flameout :	81 s
	Extent of burn (mm) :	275
	Critical flux at extinguishment (kW/m ²) :	34.29
	Heat for ignition (MJ/m ²) :	1.78
	Average heat for sustained burning (MJ/m ²) :	1.921
	Peak heat release rate (kW) :	1.05
	Time to peak heat release rate :	50 s
	Total heat release (MJ) :	0.019
	Burning droplets :	None
Test 3:	Time to ignition :	7 s
	Time to flameout :	78 s
	Extent of burn (mm) :	255
	Critical flux at extinguishment (kW/m ²) :	37.03
	Heat for ignition (MJ/m ²) :	1.874
	Average heat for sustained burning (MJ/m ²) :	1.925
	Peak heat release rate (kW) :	1.86
	Time to peak heat release rate :	49 s
	Total heat release (MJ) :	0.038
	Burning droplets :	None

Surface flammability criteria, 2010 FTP Code, Annex 1 Part 5

Bulkhead, wall and ceiling linings				Floor coverings / Prim. deck coverings			
CFE (kW/m ²)	Q _{sb} (MJ/m ²)	Q _t (MJ)	Q _p (kW)	CFE (kW/m ²)	Q _{sb} (MJ/m ²)	Q _t (MJ)	Q _p (kW)
≥ 20.0	≥ 1.5	≤ 0.7	≤ 4.0	≥ 7.0	≥ 0.25	≤ 2.0	≤ 10.0
Burning droplets:		None		≤ 10		None	