

PRODUCT DATA SHEET

SikaBond®-151

ELASTIC WOOD FLOOR ADHESIVE



DESCRIPTION

SikaBond®-151 is a 1-part wood floor adhesive for all types of wood flooring and suitable for most common types of floor substrates. The elastic adhesive is easy to spread while maintaining stable trowel peaks.

USES

Full surface bonding of wood floor types:

- Engineered wood
- Mosaic parquet
- Lamparquet (≤ 55 × 220 mm, thickness ≥ 10 mm)
- Solid planks (10 x thickness > width)

Subfloor types:

- Concrete screed
- Cement screed
- Magnesite screed
- Calcium sulphate screed
- Parquet
- Plywood
- Chipboard (V100)
- OSB

CHARACTERISTICS / ADVANTAGES

- Easy to spread
- Stable trowel peaks
- Good varnish compatibility
- Walkable after 8 hours
- Very low emissions

SUSTAINABILITY

- Conformity with LEED v4 EQc 2: Low-Emitting Materials
- VOC emission classification GEV-EMICODE EC 1^{PLUS}
- Class A+ according to French Regulation on VOC emissions
- VOC emission certificate according to AgBB und DIBt approval requirements, test report No.Z-155.10-498
- IBU Environmental Product Declaration (EPD) available

PRODUCT INFORMATION

Composition	Silane modified polymer	
Packaging	17 kg container	
	4 kg foil pack	4 foil packs per box.
	600 ml foil pack (~1,0 kg)	20 foil packs per box.
	Please contact our customer service, for information of what packaging sizes are sold in Denmark.	
Colour	Parquet brown	
Shelf life	12 months from the date of production	
Storage conditions	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +25 °C. Always refer to packaging.	

TECHNICAL INFORMATION

Shear Strength	Elastic adhesive	(ISO 17178)
Service Temperature	+5 °C min. / +40 °C max.	

APPLICATION INFORMATION

Consumption	Consumption (Full surface bonding)	V-Notched trowel type (TKB Germany)
	800–1000 g/m ²	Trowel B3
	900–1200 g/m ²	Trowel B6
	1000–1300 g/m ²	Trowel B11 / P5
When bonding long or wide boards or applying on uneven substrates a sufficient amount of adhesive must be applied to provide full surface bonding. Substrates primed with Sika® Primer MR Fast or Sika® Primer MB, may reduce the consumption.		
Sag Flow	SikaBond®-151 spreads easily while maintaining stable trowel peaks.	
Ambient Air Temperature	+15 °C min. / +35 °C max.	
Relative Air Humidity	40 % min. / 70 % max.	
Substrate Temperature	+15 °C min. / +35 °C max. (+20 °C min. / +35 °C max with underfloor heating). Temperatures should be maintained during application and until fully cured.	
Curing Time	Walkable	~8 hours
	Sandable	~12 hours
	Fully cured	~48–72 hours
	Curing times depend on environmental and subfloor conditions, adhesive layer thickness and wood flooring type. The above curing times were determined at +23 °C / 50 % r.h.	
Skin Time / Laying Time	~40 minutes (+23 °C / 50 % r.h.)	

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

General

The substrate must be sound, clean, dry and free of all contaminants such as dirt, oil, grease, cement laitance, wax, varnish, old adhesive residue and poorly bonded paint coatings which could affect adhesion.

All dust, loose and friable material must be completely removed from all surfaces before the application of SikaBond®-151, preferably by vacuum extraction equipment.

Concrete / cementitious screeds

Substrate must be ground flat to provide a smooth surface without any irregularities. Fill any voids or cavities with appropriate Sika® compatible flooring repair or levelling products.

Calcium sulphate (Anhydrite) screeds

Substrate must be ground flat to provide a smooth surface without any irregularities. Fill any voids or cavities with appropriate Sika® compatible flooring repair or levelling products.

Mastic asphalt

Prime with Sika® Primer MR Fast or Sika® Primer MB and broadcast with quartz sand. Refer to individual Product Data Sheets.

Glazed ceramic and old existing ceramic tiles

Degrease and clean with Sika® Aktivator-205. Alternatively tile surfaces must be ground to remove the glaze.

Wood

Wood types such as chipboards (V100), OSB or plywood as well as gypsum boards must be securely fixed to the substructure. Remove any surface irregularities using appropriate equipment. For floating dry-floors, contact Sika Technical Services for additional information.

Other substrate types

Contact Sika Technical Services.

Priming

SikaBond®-151 can be used without priming on concrete / cementitious/ anhydrite screeds, chipboards, concrete and ceramic tiles.

For broadcasted mastic asphalt, concrete / cementitious subfloors or screeds with excessive moisture content, old adhesive residue or weak substrates, Sika® Primer MB must be used. Refer to individual

Product Data Sheet or contact Sika Technical Services for additional information.

Before wood floors may be installed in non-insulated areas, such as basements or other areas without a damp proof membrane, Sikafloor®EpoCem must be applied and sealed with Sika®Primer MB to control the moisture. Contact Sika Technical Services for additional information.

APPLICATION METHOD / TOOLS

Reference must be made to further documentation where applicable, such as relevant method statement, application manual and installation or working instructions.

Existing sub-floors

Sub-floor has to be ready for covering at time of installation of the wood flooring to prevent adhesive adhesion failure. It is the responsibility of the wood flooring installer to confirm the sub-floor is acceptable for laying the specific type of wood flooring. The installation area's ambient conditions must also be taken into consideration with regard to the effect on the sub-floor and wood flooring. Sub-floor and timber moisture content readings together with the installation area's air humidity conditions must be satisfied before the wood flooring installation.

New screeds

Screeds have to be ready for covering at time of installation of the wood flooring to prevent adhesive adhesion failure. It is the responsibility of the wood flooring installer to confirm the screed is acceptable for laying the specific type of wood flooring. The installation area's ambient conditions must also be taken into consideration with regard to the effect on the new screed and wood flooring. New screed and timber moisture content readings together with the installation area's air humidity conditions must be satisfied before the wood flooring installation. Acceptability must also be confirmed after consultation with the customer and if necessary also with the assistance of the screed installer.

Wood flooring conditioning

The wood flooring must be conditioned in the area where it is to be installed in accordance with the manufacturer's recommendations.

Adhesive application

Onto the prepared substrate, spread SikaBond®-151 uniformly with a v-notched trowel or spreader comb directly from the product container.

Laying wood flooring

Refer to wood flooring manufacturer's recommendations for expansion gap locations and dimensions. Press the wood floor pieces firmly into the adhesive so the wood floor underside is completely covered with the adhesive. The pieces can then be adjusted into position using a rubber hammer and an impact block.

Cleaning

Fresh, uncured adhesive on the wood floor surface must be removed immediately with a clean cloth and if necessary also cleaned with Sika® Remover-208. Always test wood floor surfaces for compatibility with Sika® Remover-208 before use.

Reference must also be made to the wood flooring manufacturers cleaning recommendations.

Sanding and finishing

The floor shall not be walked on earlier than 8 hours and not sanded or mechanically polished earlier than 12 hours after installation. Refer to curing times.

CLEANING OF EQUIPMENT

Clean all tools and application equipment immediately after use with Sika® Remover-208. Once cured, hardened material can only be removed mechanically. For cleaning skin use Sika® Cleaning Wipes-100.

FURTHER INFORMATION

- Pre-treatment Sealing and Bonding Chart
- Method Statement: Full Surface Bonding

IMPORTANT CONSIDERATIONS

- Substrate moisture content measurements alone are not a sufficient basis for the wood flooring installer to decide on readiness for covering. Other tests must be considered as mentioned for existing cementitious sub-floors and new screeds. Tests must be appropriate to the type of floor covering, composition, behaviour of existing sub-floor, new screed and job site ambient conditions.
- The surface of the substrate must meet the strength requirements of the wood flooring manufacturer. Testing the tensile strength of the substrate alone is not sufficient to assess the surface condition. Additional criteria such as roughness, absorbency and cleanliness must also be evaluated. For wood floor bonding, a minimal tensile strength of $\geq 1 \text{ N/mm}^2$ is required (according to EN 13892-8). New mastic asphalt (fully broadcasted) must meet the requirements of IC 10 or IC 15 (DIN 18 354 and DIN 18 560). Old mastic asphalt must in every case be tested in several floor locations and evaluated by a specialist laboratory.
- If there is any doubt the floor substrate cannot satisfy the moisture or surface conditions, the installation must not progress. Alternative floor products that can improve the substrate conditions should be considered such as surface hardeners or thin layer overlays. Contact Sika Technical Services for additional information.
- Reference must be made to the wood flooring manufacturer's installation instructions and recommendations.
- For optimum workability, the recommended adhesive temperature is minimum +15 °C.
- Be aware of jobsite relative air humidity conditions.
- A preliminary adhesion test must be carried out before any application onto glazed tiles.
- Wood floors chemically pre-treated (e.g. those produced or treated with ammonia, wood stain, timber preservative) and woods with a relatively high oil content. Written agreement from Sika Technical Services must be obtained before using SikaBond®-151.
- Do not use on polyethylene (PE), polypropylene (PP), polytetrafluoroethylene (PTFE / Teflon), and other similar plasticised synthetic materials.
- Incompatible floor primers can negatively influence the adhesion of SikaBond®-151. Preliminary trials must be carried out before using for full application.

PRODUCT DATA SHEET

SikaBond®-151

October 2019, Version 06.01

02051202000000033

- When laying wood flooring without tongue and grooved joints, e.g. mosaic parquet floors. Avoid the adhesive extruding into the joints between the wood pieces.
- Avoid contact between any wood floor surface sealer coating and adhesive. If direct contact with the adhesive is unavoidable, then compatibility must be checked and confirmed before the use of any coatings. Contact Sika Technical Services for additional information.
- Do not expose uncured SikaBond®-151 to alcohol containing products as they may interfere with the curing reaction.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

Sika Danmark A/S
 Hirsemarken 5
 3520 Farum
 Tlf. +45 48 18 85 85
 www.sika.dk



PRODUCT DATA SHEET
SikaBond®-151
 October 2019, Version 06.01
 020512020000000033

SikaBond-151-en-DK-(10-2019)-6-1.pdf