

PRODUCT DATA SHEET

Sikagard®-6060

Sprayable bitumen based underbody coating

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Chemical base	Bitumen solution	
Color (CQP001-1)	Black	
Cure mechanism	Air-drying	
Density (uncured)	1.1 kg/l	
Solid content	65 %	
Application temperature	15 – 25 °C	
Film thickness	wet	600 µm
	dry	400 µm
Tack free time	75 minutes ^A	
Drying time	3.5 h ^A	
Service temperature	-25 – 80 °C	
Shelf life	24 months ^B	

CQP = Corporate Quality Procedure

^A) 23 °C / 50 % r. h.^B) storage between 5 °C and 25 °C
DESCRIPTION

Sikagard®-6060 is a durable, thixotropic, bitumen-based protective coating with very good rust-proofing and sound deadening properties. It is suitable for an effective vehicle underbody protection. The product can be sprayed haze free without any cob webbing and does not drip.

Sikagard®-6060 shows good adhesion on different paints, metal primers, metals and PVC without the need for pretreatment. A tough coating remains after drying, protecting metal from corrosion.

PRODUCT BENEFITS

- Outstanding application properties (no running or dripping)
- Good adhesion performance to a wide variety of substrates
- Excellent acoustic and sound damping properties
- Fast drying
- Road salt resistant
- High solid content

AREAS OF APPLICATION

Sikagard®-6060 is a spray applied anti-corrosion coating for repair and protection of non-visible areas such as wheel arches and underbody parts of vehicles that do not need to be over painted.

This product is suitable for experienced professional users only. Test with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.

CHEMICAL RESISTANCE

Sikagard®-6060 is resistant against water, sea-water, salt spray, bases and acids.

The above information is offered for general guidance only. Advice on specific applications will be given on request.

METHOD OF APPLICATION

Surface preparation

Surfaces must be clean, dry and free of rust, dust and grease. Bare metal must be pre-treated to enhance corrosion resistance (e.g. uncoated steel, etc).

Application

Sikagard®-6060 can be applied by light airless spray equipments or by air-mix guns with an air pressure of approx. 3 - 6 bar. Use either the Sika® SCP Gun (pressure cup type) or the Sika® UBC Gun (vacuum type) to apply the product.

Shake can approx. 40 times before use. Cover adjacent surfaces prior the spray process. Spray at room temperature and from a distance of approx. 25 cm in an grid motion to build up a continuous coat.

Sikagard®-6060 can be applied without dripping. If a thick layer is required, let layers dry in between. A wide variety of texture can be achieved by altering the spay technique.

Do not spray on parts of the brake, engine or exhaust system.

Removal

Uncured Sikagard®-6060 can be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once dried, the material can only be removed mechanically. Hands and exposed skin shall be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water. Do not use solvents on skin.

Overpainting

Sikagard®-6060 cannot be overpainted.

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets

PACKAGING INFORMATION

Can	1 l
Jerry can	10 l
Drum	60 l

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

DISCLAIMER

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

PRODUCT DATA SHEET

Sikagard®-6060
Version 02.01 (03 - 2023), en_DK
013913010603001000

Sika Danmark A/S

Hirsemarken 5
3520 Farum
Tlf. +45 48 18 85 85
www.sika.dk

