

**BUILDING TRUST** 

# PRODUCT DATA SHEET Sikaflex<sup>®</sup>-118 Extreme Grab

## CONSTRUCTION ADHESIVE



Sikaflex<sup>®</sup>-118 Extreme Grab is a 1- part construction adhesive with very high initial grab which bonds most construction material substrates. Internal and external use.

# USES

An adhesive to bond most construction components and materials such as:

- Concrete
- Masonry
- Most stones
- Ceramic
- Wood
- Metals
- Glass
- Mirrors

# **CHARACTERISTICS / ADVANTAGES**

- Very high initial grab
- Fixing of heavy objects without temporary fixation
- Good workability
- Very low emissions
- Adhesive-sealant with CE marking
- The product is listed in the database for building products that can be used in Nordic Swan Ecolabelled buildings.

## SUSTAINABILITY

- Conformity with LEED v4 EQc 2: Low-Emitting Materials
- VOC emission classification GEV-EMICODE EC 1<sup>PLUS</sup>
- VOC emission classification of building materials RTS M1
- Class A+ according to French Regulation on VOC emissions

# **APPROVALS / CERTIFICATES**

 CE Marking and Declaration of Performance to EN 15651-1 - Sealants for non-structural use in joints in buildings - Facade elements: Class F EXT-INT CC 20HM

# **PRODUCT INFORMATION**

Composition	Silane terminated polymer
Packaging	290 ml cartridge, 12 cartridges per box
Colour	White, concrete grey, black Please contact our customer service, for information of which colors are sold in Denmark.
Shelf life	12 months from the date of production

PRODUCT DATA SHEET Sikaflex®-118 Extreme Grab July 2020, Version 06.02 02051302000000046 The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +25 °C. Always refer to packaging.

Density	~1,40 kg/l

(ISO 1183-1)

## **TECHNICAL INFORMATION**

Shore A hardness	~50 (after 28 d)	(ISO 868)
Tensile strength	~2,2 N/mm²	(ISO 37)
Tensile strain at break	~350 %	(ISO 37)
Tear propagation resistance	~10,0 N/mm	(ISO 34)
Service temperature	–40 °C min. / +80 °C max.	

## **APPLICATION INFORMATION**

Yield	Yield	Dimension	
	1 Cartridge (290 ml)		
	~100 spots	Diameter = 30 mm	
		Thickness = 4 mm	
	~5 m bead *	Nozzle diameter = 5 mm	
		(~60 ml per linear meter)	
	* Note: For heavy objects more or thicker beads (up to ~120 ml per linea metre) maybe required.		
Sag flow	0 mm (20 mm profile, 23 °C)	0 mm (20 mm profile, 23 °C) (ISO 7390)	
Ambient air temperature	+5 °C min. / +40 °C max.	+5 °C min. / +40 °C max.	
Substrate temperature	+5 °C min. / +40 °C max., min. 3	+5 °C min. / +40 °C max., min. 3 °C above dew point temperature	
Curing rate	~3 mm/24 h (23 °C / 50 % r.h.)	Sika Corporate Quality Procedure (CQP 049-2)	
Skinning time	~15 min (23 °C / 50 % r.h.)	(CQP 019-1)	

# **APPLICATION INSTRUCTIONS**

#### SUBSTRATE PREPARATION

The substrate must be sound, clean, dry and free of all contaminants such as dirt, oil, grease, cement laitance, old sealants and poorly bonded paint coatings which could affect adhesion of the adhesive.

For optimum adhesion and critical, high performance applications the following priming and/or pre-treatment procedures shall be followed:

#### Non-porous substrates

Aluminium, anodised aluminium, stainless steel, galvanised steel, powder coated metals or glazed tiles, slightly roughen surface with a fine abrasive pad. Clean and pre-treat using Sika<sup>®</sup> Aktivator-205 applied with a clean cloth.

Before bonding / sealing, allow a waiting time of > 15 minutes (< 6 hours).

Other metals, such as copper, brass and titanium-zinc, clean and pre-treat using Sika® Aktivator-205 applied with a clean cloth. After a waiting time of > 15 minutes (< 6 hours). Apply Sika® Primer-3 N applied by brush. Allow a further waiting time of > 30 minutes (< 8

hours) before bonding / sealing.

PVC has to be cleaned and pre-treated using Sika<sup>®</sup> Primer-215 applied with a brush. Allow a waiting time of > 15 minutes (< 8 hours) before bonding / sealing.

## Porous substrates

Concrete, aerated concrete and cement based renders, mortars and bricks, prime surface using Sika<sup>®</sup> Primer-3 N applied by brush.

Before bonding / sealing, allow a waiting time of > 30 minutes (< 8 hours).

For more detailed advice and instructions contact Sika Technical Services.

Note: Primers are adhesion promoters and not an alternative to improve poor preparation / cleaning of joint surfaces. Primers also improve the long term adhesion performance of a sealed joint.

#### **APPLICATION METHOD / TOOLS**

#### **Bonding Procedure**

After the necessary substrate preparation, prepare the end of the cartridge before or after inserting into the sealant gun then fit the nozzle.

Apply in triangular beads, strips or spots at intervals of



**Jika**®

**BUILDING TRUST** 

a few centimetres each. Use hand pressure only to fix the components to be bonded into position before skinning of the adhesive occurs. Incorrectly positioned components can easily be unbonded and repositioned during the first few minutes after application. If necessary, use temporary adhesive tapes, wedges, or supports to hold the assembled components together during the initial curing time.

Fresh, uncured adhesive remaining on the surface must be removed immediately. Final strength will be reached after complete curing of Sikaflex®-118 Extreme Grab, i.e. after 24 to 48 hours at +23 °C, depending on the environmental conditions and adhesive layer thickness.

### **CLEANING OF EQUIPMENT**

Clean all tools and application equipment immediately after use with Sika® Remover-208. Once cured, hardened material can only be removed mechanically. For cleaning skin use Sika® Cleaning Wipes-100.

## FURTHER INFORMATION

Pre-treatment Chart Sealing and Bonding

# IMPORTANT CONSIDERATIONS

- For good workability, the adhesive temperature shall be +20 °C.
- Application during high temperature changes is not recommended (movements during the curing).
- Before bonding, check adhesion and resistance of paints and coatings by carrying out a trail.
- Sikaflex®-118 Extreme Grab can be overpainted with most conventional water-based coating and paint systems. However, paints must first be tested to ensure compatibility by carrying out preliminary trials. The best over-painting results are obtained when the adhesive is allowed to fully cure first. Note: non-flexible paint systems may impair the elasticity of the adhesive and lead to cracking of the paint film.
- Colour variations may occur due to exposure to chemicals, high temperatures and/or UV-radiation (especially with the colour shade white). However, a change in colour is purely of aesthetic nature and does not adversely influence the technical performance or durability of the product.
- Always use Sikaflex<sup>®</sup>-118 Extreme Grab in conjunction with mechanical fixings for overhead applications or heavy items.
- For very heavy components provide temporary support until Sikaflex®-118 Extreme Grab has fully cured.
- Full surface applications / fixings are not recommended since the inner part of the adhesive layer may never cure.

- Before using on natural stone, contact Sika Technical Service.
- Do not use on bituminous substrates, natural rubber, EPDM rubber or on any building materials which might leach oils, plasticizers or solvents that could attack the adhesive.
- Do not use on polyethylene (PE), polypropylene (PP), polytetrafluoroethylene (PTFE / Teflon), and certain plasticised synthetic materials. Preliminary trials shall be carried out or contact Sika Technical Services.
- Do not use for glass bonding if the bond line is exposed to sunlight.
- Do not use for structural bonding.
- Do not expose uncured Sikaflex<sup>®</sup>-118 Extreme Grab to alcohol containing products as this may interfere with the curing reaction.

# **BASIS OF PRODUCT DATA**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

# LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

# ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

# LEGAL NOTES

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product have been given in good faith based on our own experiences and based of approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering

**BUILDING TRUST** 

PRODUCT DATA SHEET Sikaflex®-118 Extreme Grab July 2020, Version 06.02 02051302000000046



the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

**Sika Danmark A/S** Hirsemarken 5 3520 Farum Tlf. +45 48 18 85 85 www.sika.dk



 PRODUCT DATA SHEET

 Sikaflex®-118 Extreme Grab

 July 2020, Version 06.02

 02051302000000046

Sikaflex-118ExtremeGrab-en-DK-(07-2020)-6-2.pdf



**BUILDING TRUST**