

PRODUCT DATA SHEET

SikaPower®-4720

2-component high-strength panel adhesive

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Properties	SikaPower®-4720 A	SikaPower®-4720 B
Chemical base	Epoxy	Amine
Color (CQP001-1)	Black	Tan
Density	1.08 kg/l	1.13 kg/l
Mixing ratio	A:B by volume 2 : 1	
Non-sag properties	Good	
Application temperature	10 – 30 °C	
Open time (CQP580-1, -6 / ISO 4587)	60 minutes ^A	
Mixer open time	30 minutes ^A	
Clamp time (CQP580-1, -6)	time to reach 1 MPa 4.5 hours ^{A/B}	
Curing time	80 % of strength 24 hours ^A	
Shore D hardness (ASTM D2240)	80	
Tensile strength (CQP580-5)	24 MPa	
Young's - modulus (CQP580-1, -6)	1900 MPa	
Elongation at break (ASTM D638)	3 %	
STOP-using-Impact peel strength (CQP580-1, -3)	12 N/mm	
Glass transition temperature (ASTM E-1640)	73 °C	
Thermal resistance (CQP 513-1)	1 hour 190 °C	
Service temperature	-30 – 120 °C	
Shelf life	24 months	

CQP = Corporate Quality Procedure

A) 23 °C / 50 % r.h.

B) Substrate 0.8 mm steel type DC04

DESCRIPTION

SikaPower®-4720 is a 2-component high-strength epoxy adhesive with very good adhesion properties on a wide variety of substrates. It is specifically designed for metal and composite panel bonding. The glass beads guarantee a uniformed and optimal bond line thickness of 0.25 mm. The adhesive cures at room temperature to form a rigid bond.

PRODUCT BENEFITS

- High strength adhesion performance
- Good adhesion to a wide variety of substrates without primer
- Long open time
- Fast curing property
- No running or dripping
- Can be spot welded (uncured)
- Engineered for optimum bond line thickness
- Accelerated curing with heat
- Low odor
- Very good corrosion protection
- Solvent free

AREAS OF APPLICATION

SikaPower®-4720 is suitable for panel bonding with exposure to high dynamic stress areas such as door skins, rear body panels, roof skins or quarter panels. Use for body structure parts only in combination with spot welds or rivets, following vehicle manufacturers recommendation. Common substrates are metals, particularly aluminum (incl. anodized and rolled), cold rolled steel and FRP-substrates.

Metal sheets assembled with SikaPower®-4720 (in uncured stage) can be spot welded. This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed ensuring adhesion and material compatibility.

PRODUCT DATA SHEET

SikaPower®-4720

Version 04.01 (08 - 2024), en_DK

013106477200001000

CURE MECHANISM

The curing of SikaPower®-4720 takes place by chemical reaction of the 2 components. For indications of typical strength build-up consult the table below.

Time [h]	Lap-shear strength [MPa]			
	10 °C	23 °C	30 °C	60 °C
1	-	-	-	13
2	-	-	2.7	Final strength 14 [MPa]
4	-	0.7	12	
4.5	-	1.2		
6	-	3		
8	0.1	6		
24	6	12		
48	12			

Table 1: Lap shear strength SikaPower®-4720

METHOD OF APPLICATION

Surface preparation

Abrade metals surfaces to bare metal, clean and degrease with Acetone or Heptane. Additional surface treatment depends on the specific nature of the substrates and the manufacturer process.

Application

SikaPower®-4720 is dispensed from 2 in 1 u-TAH cartridges with adequate piston guns. In order to achieve a proper mixing a quadro MGQ 10-19D mixer is required. At low temperatures (10 °C) cartridge needs to be warmed up prior the application to increase extrusion speed.

Extrude adhesive without mixer to equalize the filling levels, attach the mixer and dispose of the first few cm of the bead.

For corrosion protection, apply and tool the adhesive in a thin layer on both substrates covering all grinded areas. Apply an adhesive bead on one side 5 mm from the edge to reduce the material squeeze out (except the spot weld points).

Mount the spare part and add clamps at the corners first. Fix it with rivets or spot welding if required or place clamps every 10 cm. One side application will reduce the open time and final strength up to 50 % and can decrease the corrosion protection.

For detailed description of handling the cartridge and mixer as well as application process, refer to the Panel Replacement Guide, which is available via the Technical Department of Sika Industry.

SikaPower®-4720 can be applied at temperature between 10 °C and 30 °C. This temperature range is valid for the product, substrates and ambient conditions.

Curing

SikaPower®-4720 cures at ambient conditions. The curing speed depends on temperature. 10 °C higher temperatures would result approx. in doubling the curing speed and reducing the open time by 50 %. Curing speed can be accelerated by temperature (max. 85 °C) using infrared lamps or ovens.

Removal

Uncured SikaPower®-4720 can be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once cured, the material can only be removed mechanically. Hands and exposed skin have to be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water. Do not use solvents on skin.

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets
- Panel Replacement Guide

PACKAGING INFORMATION

Coaxial Cartridge	195 ml
Side-by-Side Cartridge	220 ml

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

DISCLAIMER

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

PRODUCT DATA SHEET

SikaPower®-4720

Version 04.01 (08 - 2024), en_DK
013106477200001000

