

PRODUCT DATA SHEET

Sarnacol[®]-2142 V

VOC free adhesive for Sarnafil[®] felt backed roof waterproofing membranes

DESCRIPTION

Sarnacol[®]-2142 V is a VOC free, 1-part, polyurethane based moisture curing adhesive.

USES

Bonding Sarnafil[®] G Felt-type and Sarnafil[®] T Felt-type membranes to roof substrates.

Bonding substrates:

- Concrete, lightweight concrete, plaster
- Oriented fibre strand boards, plywood panels
- Fibre cement boards
- Slated/mineralized bitumen sheets; new and aged
- Mineral fibre boards: product specific approval with sufficient compressive strength and appropriate surface for bonding
- PUR/PIR insulation boards with lamination (glass or mineral fibre fleece)
- EPS insulation boards: Slap stock foaming cut, compressive strength ≥ 100 kPa
- Steel panels: product specific approval (e.g. Brucha Panels WP)

CHARACTERISTICS / ADVANTAGES

- VOC free
- Adheres to solid, rough, clean, dry or slightly moist surfaces
- Application by roller
- Good adhesion to different substrates

PRODUCT INFORMATION

Composition	Polyurethane moisture curing	
Packaging	One way container:	10 kg
	Packing unit:	Euro pallet or single container
Appearance / Colour	Blue	
Shelf life	12 months from date of production.	
Storage conditions	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between + 5 °C and + 25 °C. Always refer to packaging.	
Density	~1,12 kg/l (+20 °C)	

PRODUCT DATA SHEET

Sarnacol[®]-2142 V

July 2021, Version 01.01

020945072000000045

Volatile organic compound (VOC) content	VOC-CH	0,0 %
	VOC-EU	0,0 %
Consistency	Liquid	

SYSTEM INFORMATION

Compatibility	Incompatible substrates: <ul style="list-style-type: none"> ▪ Single ply waterproofing membranes (thermoplastics/elastomers) ▪ Sheet metal ▪ Talcum coated bituminous sheets
---------------	--

APPLICATION INFORMATION

Consumption	<p>Consumption depends on the roughness and absorbency of the substrate. Recommended consumption of Sarnacol®-2142 V on different substrates (+20 °C / 50 % r.h.)</p> <table border="1"> <thead> <tr> <th>Substrate</th> <th>g/m²</th> </tr> </thead> <tbody> <tr> <td>Mineral-fibre board: Rockwool Bondrock MV, Multifix</td> <td>350–800</td> </tr> <tr> <td>Bituminous sheet: New/Aged: Slated/mineral surface</td> <td>250–400</td> </tr> <tr> <td>PUR/PIR: Type Kingspan TR 27 with glass tissue facing</td> <td>250–400</td> </tr> <tr> <td>Timber: OSB3</td> <td>250–400</td> </tr> <tr> <td>EPS: Prefabricated roof insulation sheets: e.g. ISOBOUW</td> <td>250–400</td> </tr> <tr> <td>Sandwich panel</td> <td>250–400</td> </tr> <tr> <td>Concrete</td> <td>250–400</td> </tr> </tbody> </table> <p>These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc.</p>	Substrate	g/m ²	Mineral-fibre board: Rockwool Bondrock MV, Multifix	350–800	Bituminous sheet: New/Aged: Slated/mineral surface	250–400	PUR/PIR: Type Kingspan TR 27 with glass tissue facing	250–400	Timber: OSB3	250–400	EPS: Prefabricated roof insulation sheets: e.g. ISOBOUW	250–400	Sandwich panel	250–400	Concrete	250–400
Substrate	g/m ²																
Mineral-fibre board: Rockwool Bondrock MV, Multifix	350–800																
Bituminous sheet: New/Aged: Slated/mineral surface	250–400																
PUR/PIR: Type Kingspan TR 27 with glass tissue facing	250–400																
Timber: OSB3	250–400																
EPS: Prefabricated roof insulation sheets: e.g. ISOBOUW	250–400																
Sandwich panel	250–400																
Concrete	250–400																
Ambient air temperature	+5 °C min																
Substrate temperature	+5 °C min																
Setting time	~0,5–2 hours. Setting is prolonged in low temperatures and accelerated in high temperatures. Final strength is achieved after ~1 week. These times can be affected by ambient conditions.																

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER INFORMATION

- Installation instructions: Sarnafil® G 410-EL Felt or Sarnafil® TG 76 Felt system fully bonded for exposed roofs

IMPORTANT CONSIDERATIONS

- The use of some ancillary products such as adhesives, cleaners and solvents is limited to temperatures above + 5 °C. Observe temperature limitations in the appropriate Product Data Sheets
- Special measures may be compulsory for installation below + 5 °C ambient temperature due to safety requirements in accordance with national regulations

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

The substrate must offer sufficient strength and adhesion to resist the forces generated by wind suction.

SUBSTRATE PREPARATION

The substrate must be firm, clean, dry or slightly moist, free from oil, grease, dust, stripping agents, standing water, bitumen residue and loose friable particles.

APPLICATION

Reference must be made to further documentation where applicable, such as relevant method statement, application manual and installation or working instructions.

General information

Sarnacol®-2142 V must be stirred carefully before use. Keep adhesive container closed whenever adhesive is not being used to prevent surface skinning. To improve the workability of the adhesive at low temperatures, the closed container can be placed in warm water (max. +40 °C). Adhesive residue on Sarnafil® G Felt must be cleaned with Sarna Cleaner. Adhesive residue on Sarnafil® T Felt, must be cleaned with Sarnafil® T Clean.

General bonding procedure - Wet bonding

The adhesive is spread evenly onto the substrate by using a synthetic application roller directly from the container and ensuring there are no lumps in the applied layers.

Bonding to PVC Membranes

Apply adhesive onto the substrate. Do not apply the adhesive to an area greater than can be covered within 15 minutes. Do not pour out the adhesive and roll in a second stage. After a few minutes (before the adhesive forms a skin), place the felt-backed membrane in position onto the wet substrate adhesive. Press down firmly on the membrane using a suitable pressure roller such as a water-filled, or heavy steel roller 40–50 kg.

Bonding to EPS insulation board

Apply adhesive onto the substrate in a thin layer (~250 g/m²).

Bonding to very absorbent substrates (Mineral fibre boards)

Apply 2 coats of adhesive. The first coat ~800 g/m². Allow the adhesive to dry completely. Apply a second coat ~400 g/m² max.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with Sarna Cleaner or Sarnafil® T immediately after use. Hardened material can only be mechanically removed.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

Sika Danmark A/S
Hirsemarken 5
3520 Farum
Tlf. +45 48 18 85 85
www.sika.dk



PRODUCT DATA SHEET

Sarnacol®-2142 V
July 2021, Version 01.01
02094507200000045

Sarnacol-2142V-en-DK-(07-2021)-1-1.pdf