

PRODUCT DATA SHEET

Sikafloor® Garage

2-part low emission water-based epoxy coating

DESCRIPTION

Sikafloor® Garage is a 2-part, epoxy, water based, coloured, floor coating that can provide a seamless, low maintenance, chemical resistant, smooth gloss finish. For normal -medium wear conditions. Internal and external use.

USES

The Product is used as a:

- Coating for concrete, cementitious screeds, Sikafloor epoxy broadcast systems and Sikadur epoxy mortars
- Normal up to medium heavy mechanical and chemical exposure

The product is used for:

- Production areas
- Warehouses
- Car park decks
- Garages with light to medium traffic

Please note:

- The Product may only be used by experienced professionals.

FEATURES

- Low VOC emissions
- Good mechanical resistance
- Good resistance to chemicals
- Water vapour permeable
- Water dilutable
- Easily applied by roller

SUSTAINABILITY

- Conforms with LEED v4 MR credit: Building product disclosure and optimization — Environmental Product Declarations (option 1)
- VOC emissions AFSSET, Sikafloor® Garage, eurofins, Report No.G20255C02
- VOC emissions, AgBB, Sikafloor® Garage, eurofins, Approval No. G20255B02
- VOC emissions, Indoor air comfort, Sikafloor® Garage, eurofins, Report No. G2025

CERTIFICATES AND TEST REPORTS

- Fire Testing EN ISO 9239-1, Sikafloor Garage, Textiles, Test report No.19-1121-1

PRODUCT INFORMATION

Composition	Water based epoxy	
Packaging	Part A	4.38 kg containers
Part B		
Part A + B		
Refer to current price list for packaging variations.		
Appearance and colour	Resin - Part A	coloured, liquid
	Hardener - Part B	white, liquid
Final floor appearance: Smooth, gloss finish Standard Colour: pebble grey (~RAL 7032) Applied colours selected from colour charts will be approximate. For colour matching: Apply colour sample and confirm colour under real lighting		

conditions.

When product is exposed to direct sunlight, there may be some discolouration and colour variation, this has no influence on the function and performance of the coating.

Product can be used outside provided discolouration is acceptable to the customer.

Shelf life	12 months from date of production		
Storage conditions	The Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging. Refer to the current Safety Data Sheet for information on safe handling and storage.		
Density	Resin	Density at +23 °C	(EN ISO 2811-1)
	Part A	~1.33 kg/L	
	Part B	~1.07 kg/L	
	Mixed resin	~1.3 kg/L	
Solid content by mass	~56 %		
Solid content by volume	~45 %		

TECHNICAL INFORMATION

Abrasion resistance	~56 mg (CS 10 /1000 g /1000 cycles) (14 days / +23 °C) (DIN 53109)		
Chemical resistance	Resistant to many chemicals. Contact Sika technical service for specific information		
Temperature resistance	IMPORTANT Exposure to moist or wet heat This product, can resist short-term moist or wet heat of up to +80 °C, if the exposure is only temporary (less than 1 hour). However, during exposure to moist or wet heat, do not also subject the Product to chemical and/or mechanical strain, as it may cause damage.		
	Exposure	Dry heat	
	Permanent	+60 °C	
	Short-term max. 7 days	+80 °C	
	Short-term max. 12 hours	+100 °C	

APPLICATION INFORMATION

Mixing ratio	Part A : Part B = 73: 27 (by weight)		
Consumption	~0.2–0.3 kg/m ² applied as a roller coating Note: Consumption data is theoretical and does not allow for any additional material due to surface porosity, surface profile, variations in level, wastage or any other variations. Apply product to a test area to calculate the exact consumption for the specific substrate conditions and proposed application equipment.		
Material temperature	Maximum	+30 °C	
	Minimum	+10 °C	
Ambient air temperature	Maximum	+30 °C	
	Minimum	+10 °C	
Relative air humidity	80 % maximum		
Dew point	Beware of condensation. The substrate and uncured applied product must be at least +3 °C above dew point to reduce the risk of condensation or blooming on the surface of the applied product. Low temperatures and		

PRODUCT DATA SHEET

Sikafloor® Garage

February 2026, Version 05.01

02081101002000012

high humidity conditions increase the probability of blooming.

Substrate temperature	Maximum	+30 °C		
	Minimum	+10 °C		
Substrate moisture content	Substrate	Test method	Moisture content	
	Cementitious substrates	Sika® Tramex moisture metre	≤ 6 %	
	Cementitious substrates	Calcium carbide method (CM-method)	≤ 4 %	
	Substrate	Test method	Moisture content	
	Magnesite screeds	Calcium carbide method (CM-method)	≤ 4 %	
	Anhydrite screeds	Calcium carbide method (CM-method)	≤ 0.3 %	
	No rising moisture (ASTM D4263, polyethylene sheet)			
Pot Life	Temperature	Time		
	+30 °C	~30 minutes		
	+20 °C	~60 minutes		
	+10 °C	~120 minutes		
Curing time	Substrate temperature	Maximum	Minimum	
	+30 °C	3 days	10 hours	
	+20 °C	6 days	20 hours	
	+10 °C	7 days	48 hours	
	Note: Times are approximate and will be affected by changing ambient conditions, particularly temperature and relative humidity.			
Applied product ready for use	Temperature	Foot traffic	Light traffic	Full cure
	+30 °C	~10 hours	~2 days	~5 days
	+20 °C	~20 hours	~3 days	~7 days
	+10 °C	~48 hours	~5 days	~10 days
	Note: Times are approximate and will be affected by changing ambient conditions, particularly temperature and relative humidity.			

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTATION

- Sika® Method Statement: Evaluation and Preparation of Surfaces for Flooring Systems
- Sika® Method Statement: Mixing & Application of Flooring Systems
- Sika® Method Statement: Sikafloor®-Cleaning Regime

IMPORTANT CONSIDERATIONS

- After application, the Product must be protected from damp, condensation and direct water contact (rain) for at least 24 hours.
- For exact colour matching, ensure the Sikafloor® Garage in each area is applied from the same control batch numbers.
- The "gloss" of the finish can vary with temperature, humidity and the absorbency of the substrate.

- When using light colour shades (such as yellow or orange), it may be necessary to apply several coats of Sikafloor® Garage to achieve full opacity (hiding power).
- Uneven application of the coating, resulting in variable coating layer thicknesses, may cause 'gloss' differences in the surface finish.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

IMPORTANT

Strictly follow installation procedures

Strictly follow installation procedures as defined in Method Statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

EQUIPMENT

Select the most appropriate equipment required for the project:

SUBSTRATE PREPARATION

- Abrasive blasting cleaning system
- Planing machine
- Scarifying machine

MIXING

- Electric double paddle mixer ~700 W (300–400 rpm)

- Scraper

- Clean mixing containers

APPLICATION

- Mixed material carrier

- Short pile (12 mm) nylon rollers

SUBSTRATE QUALITY

Cementitious substrates (concrete / screed) must be structurally sound and of sufficient compressive strength (minimum 25 N/mm²) with a minimum tensile strength of 1.5 N/mm².

Substrates must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings, laitance, surface treatments and loose friable material.

Use industrial vacuuming equipment to remove all dust, loose and friable material from the application surface before applying the Product.

TREATMENT OF JOINTS AND CRACKS

Construction joints and existing static surface cracks in substrate require pre-treating before full layer application. Use Sikadur® or Sikafloor® resins.

SUBSTRATE PREPARATION

MECHANICAL SUBSTRATE PREPARATION

IMPORTANT

Exposing blow holes and voids

When mechanically preparing the surface, make sure to fully expose blow holes and voids.

1. Remove weak cementitious substrates.
2. Prepare cementitious substrates mechanically using abrasive blast cleaning or planing / scarifying equipment to remove cement laitance.
3. Before applying thin layer resins, remove high spots by grinding.
4. Use industrial vacuuming equipment to remove all dust, loose and friable material from the application surface before applying the Product.
5. Use products from the Sikafloor®, Sikadur® and Sikagard® range of materials to level the surface or fill cracks, blow holes and voids.

Contact Sika® Technical Services for additional information on products for levelling and repairing defects.

SUBSTRATE PREPARATION OF NON-CEMENTITIOUS SUBSTRATES

For information on substrate preparation of non-cementitious substrates, contact Sika technical services.

MIXING

1. Prior to mixing all parts, mix Part A (resin) using an electric double paddle mixer. Mix liquid and all the coloured pigment until a uniform colour and mix has been achieved.
2. Add Part B (hardener) to Part A.
3. Mix Part A + B continuously for ~2 minutes until a uniformly coloured mix is achieved.
Note: Avoid excessive mixing to minimise air entrainment.
4. To ensure thorough mixing, pour materials into another container and mix again for at least 1 minute to achieve a smooth and uniform mix.
5. During the final mixing stage, scrape down the sides and bottom of the mixing container with a flat or straight edge trowel at least once to ensure complete mixing.

APPLICATION

IMPORTANT

Temporary heating

If temporary heating is required, do not use gas, oil, paraffin or other fossil fuel heaters. These produce large quantities of both carbon dioxide and water vapour, which may adversely affect the finish.

1. For heating, use only electric powered warm air blower systems.

IMPORTANT

Ventilation in confined spaces

Always ensure good ventilation when applying the Product in a confined space.

PRIMER

1. Pour mixed primer onto the prepared substrate and apply by brush, roller or squeegee.
2. Back roller in two directions at right angles to each other.
Note: Ensure a continuous, pore free coat covers the substrate. If necessary, apply two priming coats.
3. Confirm waiting / overcoating time has been achieved before applying subsequent products.
Refer to individual primer Product Data Sheet.

COATING

1. Apply the Product onto the prepared substrate using a short-piled roller in two directions at right angles to each other.
Note: A seamless finish can be achieved if a 'wet' edge is maintained during application.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use. Hardened material can only be removed mechanically.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

PRODUCT DATA SHEET

Sikafloor® Garage

February 2026, Version 05.01

020811010020000012

LEGAL NOTES

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

Sika Danmark A/S

Hirsemarken 5
3520 Farum
Tlf. +45 48 18 85 85
www.sika.dk



PRODUCT DATA SHEET

Sikafloor® Garage
February 2026, Version 05.01
020811010020000012

SikafloorGarage-en-DK-(02-2026)-5-1.pdf