

PRODUCT DATA SHEET

Sikafloor® Marine-505

WATERBASED 2-COMPONENT POLYURETHANE PIGMENTED MATT TOPCOAT FOR INTERNAL DECKS

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Properties	Sikafloor® Marine-505 (A)	Sikafloor® Marine-505 (B)
Chemical base	Acrylic dispersion	Isocyanate
Color (CQP001-1)	Colored	Transparent
Density	1.3 kg/l	1.1 kg/l
	mixed (+ 7 % H ₂ O)	1.2 kg/l
Solid content	58 %	
Mixing ratio	by weight (A:B)	85 : 15
Application temperature	substrate / climate	10 – 30 °C ^{A, B}
Coat weight	130 – 150 g/m ²	
Pot-life	at 10 °C	50 minutes
	at 20 °C	30 minutes
	at 30 °C	20 minutes
Shelf life	6 months ^C	12 months ^C

CQP = Corporate Quality Procedure^{A)} Substrate must be 3 °C above dew point

^{B)} Maximum 80 % r. h.

^{C)} stored in sealed container in up-right position in a dry place between 5 and 30 °C, protected from direct sunlight

DESCRIPTION

Sikafloor® Marine-505 is a water based 2-component polyurethane colored matt topcoat for internal decks. It is used as a component of the internal Sikafloor® Marine Deco systems.

Sikafloor® Marine-505 has been tested according to FTP Code system and approved according the IMO Marine Equipment Directives.


PRODUCT BENEFITS

- Very low VOC emission
- Good UV resistance
- IMO approved
- Excellent working characteristics
- Easy to clean

AREAS OF APPLICATION

Sikafloor® Marine-505 is designed as a component of the Sikafloor® Marine Deco systems for internal decks in ship and boat construction. This includes wet and dry areas.

This product is suitable for experienced professional users only. Test with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.



CURE MECHANISM

The curing of Sikafloor® Marine-505 takes place by a chemical reaction of the two components.

Higher temperatures speed up and lower temperatures slow down the curing process.

CHEMICAL RESISTANCE

For advice on chemical resistance contact the Technical Department of Sika Industry.

METHOD OF APPLICATION

Surface preparation

Dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush or vacuum. Ensure that substrates are clean, dry and free from all contaminants such as dirt, oil, grease, coatings and other surface treatments.

Mixing process

Prior to mixing both components, stir part A with a proper mixing paddle.

After adding part B mix continuously for 3 minutes until a uniform mix has been achieved.

To obtain a smoother surface, 5 – 7 % water can be added which would require mixing for another minute. Wait 1 minute and mix again for 1 minute. Note: Adding of water from 1 mix to another has to be very accurate or variations in finish will occur. To ensure homogenous mixing pour materials into another container and mix again for at least 1 minute.

Mix with mixing paddles not higher than 300 rpm's to minimize air entrapment.

After mixing wait 10 minutes before start working with Sikafloor® Marine-505.

Application

Prior to application confirm relative air humidity and dew point.

When starting to coat, make sure the coating rollers are well saturated with coating.

After proper mixing the product is poured and spread out on the floor in respect of the coat weight. Note: Keep an eye on the pot life since the end of the pot-life is not visible.

Roll with a larger 50 cm roller in one direction cross the working direction to eliminate lap-marks.

Always consult the most current corresponding Application Manual.

Curing

Indications regarding curing details see table below.

Temperature	Foot traffic	Light traffic	Full cure
10 °C	36 hours	48 hours	6 days
20 °C	16 hours	24 hours	4 days
30 °C	12 hours	18 hours	3 days

Removal

Uncured Sikafloor® Marine-505 can be removed from tools and equipment with water. Once cured, the material can only be removed mechanically.

Hands and exposed skin have to be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water.

Do not use solvents on skin.

Application limits

Freshly applied Sikafloor® Marine-505 must be protected from damp, condensation and water for at least 5 days. Uncured material reacts in contact with water (foaming).

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets
- Application Manual Sikafloor® Marine-505

PACKAGING INFORMATION

Sikafloor® Marine-505 (A)

Container	6 kg
-----------	------

Sikafloor® Marine-505 (B)

Container	1.5 kg
-----------	--------

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

DISCLAIMER

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.