

PRODUCT DATA SHEET

Sika® Injection-101 RC

Flexible PUR-Injection foam for temporary waterstopping

DESCRIPTION

Sika® Injection-101 RC is a low viscous, fast foaming and solvent-free water-reactive polyurethane injection foam resin, which cures to a dense flexible foam with a fine cellular structure.

USES

Sika® Injection-101 RC may only be used by experienced professionals.

- Sika® Injection-101 RC is used for the temporary waterstopping of high water intrusions in cracks, joints and cavities in concrete, brickwork and natural stonework.
- To achieve permanent watertight crack sealing, Sika® Injection-201 CE or Sika® Injection-203 should be injected subsequently.

CHARACTERISTICS / ADVANTAGES

- No reaction takes place unless it is in direct contact with water.
- Sika® Injection-101 RC can be injected as a single component system.
- The free foaming expansion in contact with water is up to 40 times.
- The reaction speed (foam formation) is influenced by the temperatures of the mixed material, the structure and the contact water, plus the hydrodynamic conditions.
- In cold temperatures (< + 10°C) Sika® Injection-101 RC can be accelerated using Sika® Injection-AC10.

APPROVALS / CERTIFICATES

German KTW drinking water certificate
German ZTV-ING chapter 3, part 5 (RISS) tested (BAST listed)

PRODUCT INFORMATION

Composition	Water reactive 2-part polyurethane resin, solvent and CFC free		
Packaging	Part A	10 or 20 kg	
	Part B	12.5 or 25 kg	
Colour	Part A	Colourless	
	Part B	Brown	
Shelf life	24 months shelf life from date of production if stored properly in undamaged, unopened, original sealed packaging.		
Storage conditions	Dry storage at temperatures from +5 °C up to +35 °C. Protect from direct sunlight and humidity.		
Density	Part A	~1.0 kg/l	(ISO 2811)
	Part B	~1.25 kg/l	
at 20 °C			

Viscosity	Part A	~140 mPa·s	(ISO 3219)
	Part B	~155 mPa·s	
at 20 °C			

TECHNICAL INFORMATION

Expansion	Expansion start	~15 s after contact with water	(EN 1406)
	Expansion end	~67 s	
at 20 °C			

APPLICATION INFORMATION

Mixing ratio

part A:part B = 1:1 by volume

Reaction time table Sika® Injection-101 RC
[PM 10081-11]

0 % Sika® Injection-AC10 ¹		
Material temperature	Expansion start	Expansion end
+5 °C	~19 sec	~79 sec
+10 °C	~17 sec	~88 sec
+20 °C	~16 sec	~70 sec

5 % Sika® Injection-AC10 ¹		
Material temperature	Expansion start	Expansion end
+5 °C	~12 s	~57 s
+10 °C	~11 s	~49 s
+20 °C	~10 s	~39 s

10 % Sika® Injection-AC10 ¹		
Material temperature	Expansion start	Expansion end
+5 °C	~9 s	~41 s
+10 °C	~8 s	~37 s
+20 °C	~7 s	~35 s

1 Dosage of Sika® Injection-AC10 in % by weight of Sika® Injection-101 RC (comp. A+B)

The given data are laboratory parameters and may deviate depending on the object and conditions on site.

Ambient air temperature	+5 °C min. / +35 °C max.
Substrate temperature	+5 °C min. / +35 °C max.
Pot Life	~2 hours (at + 20 °C) remove skin from the surface (do not mix in!)

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

IMPORTANT CONSIDERATIONS

Sika® Injection-101 RC is generally used for the temporary stopping of high water infiltration. To achieve permanent watertight crack sealing, the subsequent injection of Sika® Injection-201 CE or Sika® Injection-203 is recommended.

ECOLOGY, HEALTH AND SAFETY

APPLICATION INSTRUCTIONS

MIXING

Empty parts A and B into a mixing vessel and mix slowly and thoroughly for at least 3 min (max. 250 rpm) until homogeneous, thereby observing the safety precautions. The containers are supplied according to the required mixing ratio of 1 : 1 parts by volume. Partial quantities can be measured out in separate vessels. After mixing, pour the material into the pump's feed container, stir briefly and apply within the pot life.

After mixing, pour the material into the pump's feed container, stir briefly and use within the pot life.

If the substrate and/or ambient temperatures are < +10 °C, Sika® Injection-AC10 can be added to Sika® Injection-101 RC to accelerate the start of expansion.

APPLICATION METHOD / TOOLS

Use injection pumps suitable for single part injection products.

CLEANING OF EQUIPMENT

Clean all tools and application equipment according to the Product Data Sheet for the Sika® Injection Cleaning System.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

Sika Danmark A/S
Hirsemarken 5
3520 Farum
Tlf. +45 48 18 85 85
www.sika.dk



PRODUCT DATA SHEET
Sika® Injection-101 RC
December 2022, Version 03.01
020707010010000001

Sikalnjection-101RC-en-DK-(12-2022)-3-1.pdf