

PRODUCT DATA SHEET

Sika® Igoflex®-201

2-part polymer modified bituminous thick coating

DESCRIPTION

Sika® Igoflex®-201 is a 2 components polymer modified bituminous flexible thick coating extended with fibre for waterproofing against dampness and moisture ingress.

USES

- Waterproofing and damp proofing of below ground concrete structures to protect against percolating water, dampness and moisture ingress
- Waterproofing beneath cementitious floor screeds
- Adhesive to bond lightweight thermal insulation boards

CHARACTERISTICS / ADVANTAGES

- Non-flammable
- Flexible with crack-bridging capabilities
- Fast curing time
- Used as adhesive for thermal insulation boards
- Can be applied on dry and slightly damp surfaces
- Easy to apply by notched trowel
- Non-sag on vertical surfaces

APPROVALS / CERTIFICATES

- CE Marking and Declaration of Performance to EN 15814 - Polymer modified bituminous thick coatings for waterproofing in below ground structures

PRODUCT INFORMATION

Composition	Polymer modified and fibre reinforced bitumen emulsion and a reactive hydraulic binder.	
Packaging	32 kg combi-unit:	
	Part A - Liquid	24 kg
	Part B - Powder	8 kg
	Refer to current price list for packaging variations.	
Colour	Part A	Black
	Part B	Grey
Shelf life	12 months from date of production	
Storage conditions	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging.	
Density	Part A	~1,03 kg/l
	Part B	~1,30 kg/l
	Mixed A + B	~1,17 kg/l

TECHNICAL INFORMATION

Crack bridging ability	Class CB 2	No damage (for crack width ≥ 2 mm and dry layer thickness ≥ 3 mm)	(EN 15812)
Chemical resistance	Resistant to aggressive substances in natural ground water and soil. Contact Sika Technical Services for additional information.		
Permeability to water vapour	$\mu \geq 38\,000$		(DIN EN 12086)
	$S_d \geq 117$ m		(DIN EN 1931)
Watertightness	Class W2A	Pass (≥ 72 h at $0,075$ N/mm ² for dry layer thickness with in- lay ≥ 4 mm)	(EN 15820)
Reaction to fire	Class E		(EN 13501-1)

APPLICATION INFORMATION

Mixing ratio	Part A : Part B = 3 : 1 (by weight)		
Consumption	Consumption depends on the roughness and absorbency of the substrate. These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc.		
	Damp proofing	$\sim 4,5$ to $5,0$ kg/m ²	($\sim 4,5$ to $5,0$ mm wft) ($3,1$ to $3,4$ mm dft)
	Waterproofing	$\sim 6,0$ to $6,5$ kg/m ²	($\sim 6,0$ to $6,5$ mm wft) ($4,4$ to $4,7$ mm dft)
	Adhesive for boards	$\sim 2,0$ kg/m ²	
	These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc.		
Layer thickness	Refer to national and local standard. Minimum recommendations:		
	Damp proofing	3 mm dry film (one layer)	
	Waterproofing	4 mm dry film in two layers with an inlay of Sika® Igoflex® F-01	
Ambient air temperature	+5 °C min. / +35 °C max.		
Substrate temperature	+5 °C min. / +35 °C max.		
Substrate moisture content	Dry or slightly damp		
Pot Life	$\sim 1,5$ hours (at +20 °C), depends on ambient conditions.		
Curing time	Fully cured: ~ 2 to 3 days. Times are approximate and will be affected by substrate, film thickness and changing ambient conditions particularly temperature and relative humidity.		
Waiting time to overcoating	Sika® Igoflex®-201 on Sika® Igoflex®-201: Within 2 to 4 hours. Times are approximate and will be affected by substrate, film thickness and changing ambient conditions particularly temperature and relative humidity.		

BASIS OF PRODUCT DATA

based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

All technical data stated in this Product Data Sheet are

IMPORTANT CONSIDERATIONS

- Sika® Igoalflex®-201 is recommended for waterproofing against percolating water not water pressure.
- After application product must be protected from rain, frost and direct sunlight etc. until cured.
- Do not use on structural elements permanently exposed to UV light and weathering.
- Do not use for contact with potable drinking water.
- Coating must be protected as soon as possible after the coating has hardened and before backfilling.
- Do not use on structural elements which are exposed to vehicular or pedestrian traffic.
- Additional joint sealing using Sika® Joint Sealing Solutions is recommended for connections, around penetrations and expansion joints.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

Substrate must be uniform, dry or slightly damp, free from dust, loose material, surface contamination, existing coatings, oil, grease and other materials which could reduce adhesion of the coating. Surface defects (>5 mm) such as blowholes, voids, honeycombing, etc. must be filled / repaired with suitable Sika® repair mortars.

SUBSTRATE PREPARATION

Surfaces must be cleaned and prepared using suitable preparation techniques to provide a clean slightly textured surface. Defects should be repaired with an appropriate Sika® repair mortar. Porous substrates must be primed using Sika® Igoalflex® P-01 or use diluted Sika® Igoalflex®-101. Sika® Igoalflex®-101 : Water (1:2 by weight).

MIXING

Prior to mixing all parts, mix part A (resin) using an electric single paddle mixer (300–400 rpm) or other similar equipment. Mix liquid and all the coloured pigment until a uniform colour / mix has been achieved. Add part B (hardener) to part A and mix part A + B continuously for at least 3,0 minutes until a uniformly coloured mix has been achieved. Excessive mixing must be avoided to minimise air entrainment.

Sika Danmark A/S

Hirsemarken 5
3520 Farum
Tlf. +45 48 18 85 85
www.sika.dk



PRODUCT DATA SHEET

Sika® Igoalflex®-201
May 2022, Version 01.01
020706302000000002

During the final mixing stage, scrape down the sides and bottom of the mixing container with a straight edge trowel or spatula at least once to ensure complete mixing. Mix full units only. Mixing time for A+B = ~3,0 minutes.

APPLICATION METHOD / TOOLS

Strictly follow installation procedures as defined in method statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

Prior to application, confirm substrate moisture content, substrate and air temperatures.

Apply mixed Sika® Igoalflex®-201 onto prepared substrate and spread evenly using a suitable trowel to the required thickness in 1 or 2 layers.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use. Hardened Sika® Igoalflex®-201 can be removed with Sika® Colma - Cleaner.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

Sikalgoalflex-201-en-DK-(05-2022)-1-1.pdf