

# PRODUCT DATA SHEET

# Sarnacol®-2170

Contact adhesive for Sarnafil® felt backed roof waterproofing membranes

# **DESCRIPTION**

Sarnacol®-2170 is a 1-part, nitrile rubber based solvented contact adhesive

# **USES**

 Bonding Sarnafil® G-type and Sarnafil® G Felt-type waterproofing membranes to substrates and for perimeter and flashing details.

#### **Bonding substrates:**

- Concrete, lightweight concrete, brick, plaster
- Oriented strand boards (OSB), plywood panels
- Fibre cement boards
- Mineral fibre boards with sufficient compressive strength and appropriate surface for bonding
- Polyester, hard and soft PVC
- Galvanized steel, PVC-coated metal sheet
- PUR/PIR insulation boards with lamination (glass or mineral fibre fleece)

# **CHARACTERISTICS / ADVANTAGES**

- Proven performance over decades
- Adheres to solid, rough and clean surfaces
- Application by brush or roller
- Good adhesion to different substrates

# PRODUCT INFORMATION

Composition	Solvented nitrile rubber	
Packaging	One way container:	5 kg, 20 kg
	Packing unit:	Euro pallet or single container
Appearance / Colour	Red	
Shelf life	24 months from date of production.	
Storage conditions	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging	
Density	~0,90 kg/l (+20 °C)	
Volatile organic compound (VOC) content	VOC-CH (VOCV)	77 %
	VOC-EU (Solvent)	77 %

#### PRODUCT DATA SHEET

**Sarnacol®-2170**July 2021, Version 02.01
020945072000000004

#### SYSTEM INFORMATION

Compatibility	Shall not be used on substrates:
	<ul> <li>EPS/XPS insulation boards</li> </ul>
	<ul> <li>Copper plate</li> </ul>
	<ul> <li>Bituminous substrates</li> </ul>
	<ul> <li>Waterproofing membranes (thermoplastics/elastomers) excluding soft</li> </ul>
	PVC
	These materials could adversely affect the product properties.

#### APPLICATION INFORMATION

Consumption	~300 g/m²–500 g/m² up to 1000 g/m² on very absorbent substrates. Consumption depends on the roughness and absorbency of the substrate. These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc.	
Ambient air temperature	+5 °C min	
Substrate temperature	+5 °C min	
Setting time	Full adhesion is generally achieved immediately after bonding. For the wet bonding process, allow a setting time of 15 minutes to 1 hour. Final strength is achieved after ~1 week. All these times can be affected by ambient conditions.	

#### **BASIS OF PRODUCT DATA**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

# **FURTHER INFORMATION**

 Installation instructions and Product Data Sheet of the relevant roof waterproofing membrane.

#### **IMPORTANT CONSIDERATIONS**

- The use of some ancillary products such as adhesives, cleaners and solvents is limited to temperatures above +5 °C. Observe temperature limitations in the appropriate Product Data Sheets.
- Special measures may be compulsory for installation below +5 °C ambient temperature due to safety requirements in accordance with national regulations.

# **ECOLOGY, HEALTH AND SAFETY**

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

#### APPLICATION INSTRUCTIONS

# SUBSTRATE QUALITY

The substrate must offer sufficient strength and adhesion to resist the forces generated by wind suction.

#### SUBSTRATE PREPARATION

The substrate must be resistant to solvents and must be firm, clean, dry, free from oil, grease, dust, stripping agents and loose friable particles. Sheet metal must be cleaned with Sarna Cleaner before adhesive is applied.

#### **APPLICATION**

Reference must be made to further documentation where applicable, such as relevant method statement, application manual and installation or working instructions.

#### **General information**

Sarnacol®-2170 must be stirred carefully before use. Keep adhesive container closed whenever adhesive is not being used to keep workability constant (to reduce solvent evaporation).

Viscosity of the Sarnacol®-2170 contact adhesive can be changed and adapted by adding Sarna Cleaner. It may be necessary to modify the viscosity after prolonged storage or if container was opened for long periods of time. Mix Sarna Cleaner into the adhesive by carefully stirring small quantities into the adhesive to achieve the desired viscosity.

Use Sarna Cleaner to remove adhesive residue from the roof membrane.

Contact bonding procedure (Sarnafil® G-types on substrates and for perimeter / flashing details)
Spread adhesive evenly onto the substrate using an application roller. Do not apply the adhesive to an area greater than can be covered in one day. Allow the



adhesive to dry completely. Apply 2 coats of adhesive on absorbent substrates (the first coat must be completely dry before the second is applied).

Apply the adhesive evenly on the underside of the roof membrane (note: welding seam overlap area must be free of adhesive). Once the adhesive has been allowed to evaporate sufficiently (finger test), apply the membrane onto the substrate adhesive. Press down firmly on the membrane using a suitable pressure roller.

At locations which will be exposed to stresses immediately after bonding (edges), Sarnafil® G-types can also be heated externally by means of a heat source (Sarnafil® heat gun) then pressed down immediately using a suitable pressure roller.

Wet bonding procedure (Sarnafil® G Felt-types on substrates)

Spread adhesive evenly onto the substrate using an application roller. Do not apply the adhesive to an area greater than can be covered in one day. Allow the adhesive to dry completely. Apply a second coat of adhesive over the substrate. Apply the membrane onto the wet substrate adhesive. Press down firmly on the membrane using a suitable pressure roller.

#### **CLEANING OF EQUIPMENT**

Clean all tools and application equipment with Sika® Sarna Cleaner immediately after use. Hardened material can only be mechanically removed

# **LOCAL RESTRICTIONS**

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

#### **LEGAL NOTES**

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

Sika Danmark A/S Hirsemarken 5 3520 Farum

Tlf. +45 48 18 85 85 www.sika.dk







PRODUCT DATA SHEET Sarnacol®-2170 July 2021, Version 02.01 020945072000000004



Sarnacol-2170-en-DK-(07-2021)-2-1.pdf