

PRODUCT DATA SHEET

Sikadur[®]-31+

Low-VOC epoxy adhesive for structural bonding and concrete repair

DESCRIPTION

Sikadur[®]-31+ is a 2-part, low-VOC, moisture-tolerant epoxy structural adhesive which bonds to many construction materials. It is also used for structural concrete repairs, joint filling, and crack sealing. It can be used in both do-it-yourself (DIY) applications and professional applications.

USES

The Product is used as an adhesive for:

- Structural concrete repair (Principle 3, Method 3.1 of EN 1504-9). Repair of spalling and damaged concrete in buildings, bridges, infrastructure and superstructure works
- Structural strengthening (Principle 4, Method 4.3 of EN 1504-9). Bonding plate reinforcement
- Structural strengthening (Principle 4, Method 4.4 of EN 1504-9). Increasing the bearing capacity of the concrete structure by adding mortar

The Product is used for bonding the following materials:

- Concrete
- Natural stone
- Ceramics
- Fibre cement
- Mortar
- Brick masonry
- Brick slips
- Steel
- Iron
- Wood

The Product is used for repairing and reprofiling:

- Structural concrete elements such as beams, columns, and walls
- Non-structural concrete elements
- Small patches and edges

The Product is used for filling and sealing:

- Joint arrises
- Crack arrises
- Non-structural static cracks

- Holes
- Voids

FEATURES

- Easy to mix and apply
- Very low VOC (GEV Ecode EC1^{PLUS})
- Very good adhesion to many construction materials
- Very good initial and ultimate mechanical strength
- Suitable for structural concrete repair, class R4 according to EN 1504-3:2005 (Structural and non-structural repair)
- Good adhesion to dry and damp concrete
- Thixotropic: non-sag in vertical and overhead applications
- No primer required
- Good resistance to abrasion
- Good resistance to specific chemicals
- Differently coloured components for mixing control
- Impermeable to most liquids and water vapour
- Hardens without shrinkage
- Application up to 30 mm thickness in one layer
- Temperature application range +10 °C to +30 °C

SUSTAINABILITY

- Contributes towards satisfying Materials and Resources (MR) Credit: Building product disclosure and optimization — Environmental Product Declarations under LEED® v4
- Contributes towards satisfying Materials and Resources (MR) Credit: Building Product Disclosure and Optimization — Material Ingredients under LEED® v4
- Contributes towards satisfying Indoor Environmental Quality (EQ) Credit: Low-Emitting Materials under LEED® v4
- Environmental Product Declaration (EPD) in accordance with EN 15804. EPD independently verified by Institut für Bauen und Umwelt e.V. (IBU)
- VOC emission classification GEV Emicode EC1^{plus}

CERTIFICATES AND TEST REPORTS

- CE marking and declaration of performance based on EN 1504-3:2005 Products and systems for the protection and repair of concrete structures — Structural and non-structural repair
- CE marking and declaration of performance based on EN 1504-4:2004 Products and systems for the protection and repair of concrete structures — Structural bonding

PRODUCT INFORMATION

Product declaration	<ul style="list-style-type: none"> ▪ Complies with the general requirements of EN 1504-3: Class R4 ▪ Complies with the general requirements of EN 1504-4: Structural bonding for bonded plate reinforcement and bonded mortar or concrete 		
Composition	Epoxy resin and selected fillers		
Packaging	1.2 kg (A+B) container	8 × 1.2 kg carton box	
		32 boxes per pallet	256 pieces
	6 kg (A+B) container	96 containers per pallet	
	20 kg (A) container	22 containers (A) per pallet	
	10 kg (B) container	44 containers (B) per pallet	
	Refer to the current price list for available packaging variations.		
Shelf life	24 months from date of production		
Storage conditions	<p>The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging.</p> <p>Refer to the current Safety Data Sheet for information on safe handling and storage.</p>		
Colour	Part A	White	
	Part B	Dark grey	
	Part A+B mixed	Concrete grey	
Density	Mixed resin (2.00 ± 0.1) kg/l Density value at +23 °C.		
Volatile organic compound (VOC) content	Compliant with VOC emission classification GEV-Emicode EC1 ^{PLUS}		

TECHNICAL INFORMATION

Compressive strength	Class R4				(EN 1504-3)
	~75 MPa				(EN 12190)
	Curing time	+10 °C	+23 °C	+30 °C	(EN 196-1)
	1 day	-	50 MPa	50 MPa	
	3 days	50 MPa	65 MPa	70 MPa	
	7 days	70 MPa	75 MPa	78 MPa	
Tensile strength	Curing time	+10 °C	+23 °C		
	1 day	-	8.5 MPa		
	3 days	6 MPa	16 MPa		
	7 days	16 MPa	20 MPa		

PRODUCT DATA SHEET

Sikadur®-31+

July 2023, Version 04.01

020204030010000228

BUILDING TRUST



Modulus of elasticity in tension	9 GPa (7 days at +23 °C)	(EN ISO 527-2)
Tensile strain at break	0.3 % (7 days at +23 °C)	(EN ISO 527-2)
Shear strength	16 MPa	(EN 12615)
	50°	35 MPa (EN 12188)
	60°	30 MPa
	70°	25 MPa
Tensile adhesion strength	Pass	(EN 12636)
	Curing Time	Substrate
	Curing Temperature	Adhesion strength
	7 days	Concrete dry
	7 days	Concrete mat damp
	7 days	Steel
		+23 °C
		+23 °C
		+23 °C
		> 5 MPa *
		> 5 MPa *
		> 20 MPa
	* 100% concrete failure	
Shear adhesion strength	50°	≥ 60 MPa (EN 12188)
	60°	≥ 70 MPa
	70°	≥ 80 MPa
Shrinkage	~0.01 %	(EN 12617-1)
	3.0 MPa (Restrained shrinkage / expansion)	(EN 12617-4)
Coefficient of thermal expansion	4.8 × 10 ⁻⁵ (±0.2 × 10 ⁻⁵) 1/K	(EN 1770)
Glass transition temperature	50 °C	(EN 12614)
Thermal compatibility	Freeze and thaw	3.00 MPa (EN 13687-1)
	Durability	Pass (EN 13733)
Chemical resistance	Resistant to many chemicals. Contact Sika Technical Services for additional information.	
Resistance to moisture	Sensitivity to water	Pass (EN 12636)
Reaction to fire	Class C-s1, d0 Class B _{fl} -s1	(EN 13501-1)

APPLICATION INFORMATION

Mixing ratio	Part A : Part B = 2 : 1 by weight or volume
Consumption	2.0 kg/m ² per mm of thickness. Note: Consumption data is theoretical and does not allow for any additional material due to surface porosity, surface profile, variations in level, wastage or any other variations. Apply product to a test area to calculate the exact consumption for the specific substrate conditions and proposed application equipment.
Layer thickness	30 mm max. For non-structural adhesive or other applications, if layer thickness's of >30 mm are required, apply in successive 30 mm layers or once the previous layer has hardened. The surface of the freshly applied intermediate layers should be scratched to form a key for subsequent layers. If layer application is to be longer than 2 days, the wet applied adhesive must be blinded to excess with quartz sand immediately after application
Sag flow	Non-sag up to 20 mm thickness on vertical surfaces (EN 1799)

Material temperature	Maximum	+30 °C
	Minimum	+10 °C
Ambient air temperature	Maximum	+30 °C
	Minimum	+10 °C
Dew point	Beware of condensation. Steel substrate temperature during application must be at least +3 °C above dew point.	
Substrate temperature	Maximum	+30 °C
	Minimum	+10 °C
Substrate moisture content	Substrates must be dry or matt damp (no standing water). Brush the adhesive well into the substrate if matt damp.	
Pot Life	Temperature	Pot Life (ISO 9514)
	+23 °C	~60 min
	+30 °C	~45 min
Open Time	Temperature	Open Time (EN 12189)
	+23 °C	~75 min
	+30 °C	~45 min

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT

Damage due to excessive long-term load

Sikadur® resins are formulated to have low creep under long-term load. However, due to the creep behaviour of all polymer materials under load, the long-term structural design load must account for creep.

a) Ensure that the long-term structural design load is lower than 20 % to 25 % of the short-term failure load.

b) Consult a structural engineer for calculating the admissible load for the specific application.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

CONCRETE, MASONRY, MORTAR, STONE

Concrete and mortar must be at least 28 days old. Substrates must be sound, clean, dry or matt damp but free of standing water. Substrates must be free of contaminants such as ice, dirt, oil, grease, coatings, laitance, efflorescence, surface treatments and loose friable material.

STEEL

Surfaces must be sound, clean, dry and free of contaminants such as dirt, oil, grease, coatings and loose friable material.

WOOD

Surfaces must be sound, clean, dry and free of contaminants such as dirt, oil, grease, coatings and loose friable material.

SUBSTRATE PREPARATION

IMPORTANT

Reduced adhesion due to surface contamination

Surface contaminants such as dust and loose material, including the contaminants generated during substrate preparation, can reduce the Product's performance.

1. Before applying the Product, clean thoroughly all substrate surfaces using vacuum or dust removal equipment.

CONCRETE, MASONRY, MORTAR OR STONE

Suitable techniques for substrate preparation include the following:

- Abrasive blast cleaning
- Needle gunning
- Light scabbling
- Bush hammering
- Grinding

1. Prepare the substrate mechanically using a suitable technique.

The substrate has an open-textured, gripping surface profile.

PRODUCT DATA SHEET

Sikadur®-31+

July 2023, Version 04.01

020204030010000228

STEEL

Suitable techniques for substrate preparation include the following:

- Abrasive blast cleaning
- Rotating wire brush
- Grinding

1. Prepare the substrate mechanically using a suitable technique.

The substrate has a bright metal finish with a surface profile to satisfy the necessary tensile adhesion strength requirement.

WOOD

1. Prepare the substrate by planing, sanding or using other suitable equipment.

MIXING

IMPORTANT

Poor workability and unfavourable handling time due to wrong mixing

1. When using multiple units during application, do not mix the following unit until the previous unit has been used.

PRE-BATCHED UNITS

1. **IMPORTANT** Mix full units only. Prior to mixing all parts, mix part A (resin) briefly using a mixing spindle attached to a slow-speed electric mixer (max. 300 rpm).
2. Add part A to part B (hardener) and mix parts A+B continuously for at least 3 minutes until a uniformly coloured, smooth consistency mix has been achieved.
3. **IMPORTANT** Do not overmix. To ensure thorough mixing, pour materials into a clean container and mix again for approximately 1 minute. Mixing time for A+B = 4 minutes.

APPLICATION

IMPORTANT

Damage due to unsupported heavy components applied vertically or overhead

Full adhesion is not achieved before the Product has fully hardened. Hardening depends on ambient temperatures. Unsupported heavy components might fall down when not supported.

1. Provide temporary support for heavy components until the Product has fully hardened.

BONDING

Preconditions: Prior to application confirm dew point conditions before and during application.

1. **IMPORTANT** On damp prepared concrete substrates, always apply the Product by brush and work the Product well into the substrate. Apply the mixed adhesive to the prepared surfaces with a spatula, trowel, notched trowel or by gloved hand.
2. For optimum adhesion apply the adhesive to both surfaces that require bonding.
3. For heavy components positioned vertically or overhead, provide temporary support until the Product has fully hardened.

REPAIR

Preconditions: Prior to application confirm dew point conditions before and during application.

1. Place temporary formwork as required.
2. **IMPORTANT** On damp prepared concrete substrates, always apply by brush and work the Product well into the substrate. Apply the mixed adhesive to the prepared surfaces with a spatula, trowel or by gloved hand.

For repairs greater than 30 mm deep the Product must be applied in layers.

1. Roughen the surface of the freshly applied intermediate layer by scratching it to enable better adhesion of the subsequent layer.
2. Apply subsequent layers once the previous layer has hardened.
3. If the time between layers is going to be more than 2 days, blind the wet adhesive to excess with quartz sand immediately after application.

JOINT FILLING AND CRACK SEALING

1. Apply the mixed adhesive to the prepared surfaces with a spatula or trowel.

PRODUCT DATA SHEET

Sikadur®-31+

July 2023, Version 04.01
020204030010000228

CLEANING OF EQUIPMENT

Clean all tools and application equipment with Sika® Colma Cleaner immediately after use. Hardened material can only be removed mechanically.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

Sika Danmark A/S
Hirsemarken 5
3520 Farum
Tlf. +45 48 18 85 85
www.sika.dk



PRODUCT DATA SHEET

Sikadur®-31+

July 2023, Version 04.01
020204030010000228

Sikadur-31+-en-DK-(07-2023)-4-1.pdf