

BUILDING TRUST

PRODUCT DATA SHEET

Sika® FloorJoint EX

CARBON FIBRE PREFABRICATED FLOOR JOINT PANEL

DESCRIPTION

Sika® FloorJoint EX is a carbon fibre reinforced polymer (CFRP) composite, prefabricated, floor joint with high mechanical resistance for normal up to medium wear loading conditions. Its sinusoidal surface tooth profile allows for an improved load distribution and results in minimum vibrations under direct car and forklift traffic. The eccentrically arranged teeth rest completely on the opposite side of the joint even when the joint is widened. The joint is easy and quickly to install and reduces vibrations from all types of wheel loadings.

Sika® FloorJoint EX is the main part of the Sika® Floor-Joint PB-30 EX System.

USES

Sika® FloorJoint EX may only be used by experienced professionals.

- Floor joint panel for new build and refurbished joints in concrete / concrete screeds in:
- Storage areas, assembly halls, maintenance workshops, hospitals, schools, warehouses, show rooms, pharmaceutical industry, production etc.

CHARACTERISTICS / ADVANTAGES

- Grindable profile for level integration into the floor surface
- Reduced vibrations under direct car and fork lift traffic
- Thermal expansion coefficient similar to resin based floors
- Easy to install / Easy to repair
- Short down time Trafficable after 24 hrs
- Waterproof system design possible
- High chemical resistance
- Non corroding
- High mechanical resistance

APPROVALS / CERTIFICATES

- Fire Testing DIN EN 13501-1, Sika* FloorJoint, Hoch, Test report No. PB-Hoch-140803-3
- Fire Testing DIN EN ISO 11925-2, Sika* FloorJoint, Hoch, Test report No. PB-Hoch-140801-3
- Fire Testing DIN EN ISO 9239-1, Sika* FloorJoint, Hoch, Test report No. PB-Hoch-140802-3

PRODUCT INFORMATION

Composition	Carbon fibre reinforced polymer
Packaging	84 pieces on an EU-pallet. Weight: approx. 11,0 kg/piece. Please contact our customer service, for information of what packaging sizes are sold in Denmark.
Appearance / Colour	approx. RAL 7037
Shelf life	3 years from the date of production

PRODUCT DATA SHEET

Sika® FloorJoint EXApril 2020, Version 03.01
020816140020000005

Width 255 mm Height 20 mm TECHNICAL INFORMATION Compressive Strength ~80 N/mm² (after 14 days at 23 °C / 50 % r.h) (DIN EN 19 Reaction to Fire Bfl s1 (composite material of panel) (EN 1330 Chemical Resistance Resistant to many chemicals. Contact Sika Technical Services for specific formation. Opening Size For gaps in the substrate with a maximum width of 50 mm. Maximal ho zontal positive joint movement = 20 mm Joint Design Max. gap width1 Positive joint movement3 50 mm +20 mm -10 mm 1. Width of the gap in the concrete below Sika* floor Joint panel during stallation. 2. Positive joint movement is the amount the gap can open, compared to original width during installation of the Sika* floor Joint panel. Don't ceed the maximum positive joint movement capacity, otherwise the teeth of the Sika* floor Joint panel will become unsupported and mar damaged. 3. Negative joint movement is the amount the gap can close, compared its original width during installation of the Sika* floor Joint panel. Note: The sealant may break at a positive joint movement of approx. 15–20 mm, however this does not affect the technical performance of Sika* FloorJoint EX. The purpose of the joint sealant is the reduction of pick-up in the joint, not to provide water tightness. Install Sikadur* Com biflex* SG System below Sika* FloorJoint EX if a waterproof joint design required.	Storage conditions	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +35 °C and must always be stored in the horizontal position in order to avoid bending. Always refer to packaging.				
TECHNICAL INFORMATION Compressive Strength ~80 N/mm² (after 14 days at 23 °C / 50 % r.h) (DIN EN 19 Reaction to Fire Bfl s1 (composite material of panel) (EN 1330 Chemical Resistance Resistant to many chemicals. Contact Sika Technical Services for specific formation. Opening Size For gaps in the substrate with a maximum width of 50 mm. Maximal ho zontal positive joint movement = 20 mm Joint Design Max. gap width1 Positive joint movement2 ment3 50 mm +20 mm -10 mm 1. Width of the gap in the concrete below Sika® floor Joint panel during stallation. 2. Positive joint movement is the amount the gap can open, compared original width during installation of the Sika® floor Joint panel. Don't ceed the maximum positive joint movement capacity, otherwise the teeth of the Sika® floor Joint panel will become unsupported and mar damaged. 3. Negative joint movement is the amount the gap can close, compared its original width during installation of the Sika® floor Joint panel. Note: The sealant may break at a positive joint movement of approx. 15–20 mm, however this does not affect the technical performance of Sika® FloorJoint EX. The purpose of the joint sealant is the reduction of pick-up in the joint, not to provide water tightness. Install Sikadur® Com biflex® SG System below Sika® FloorJoint EX if a waterproof joint design required.	Dimensions	Length 1 200 mm		m		
TECHNICAL INFORMATION Compressive Strength ~80 N/mm² (after 14 days at 23 °C / 50 % r.h) (DIN EN 19 Reaction to Fire Bfl s1 (composite material of panel) (EN 1330 Chemical Resistance Resistant to many chemicals. Contact Sika Technical Services for specific formation. Opening Size For gaps in the substrate with a maximum width of 50 mm. Maximal ho zontal positive joint movement = 20 mm Joint Design Max. gap width1 Positive joint movement3 50 mm +20 mm 1. Width of the gap in the concrete below Sika® floor Joint panel during stallation. 2. Positive joint movement is the amount the gap can open, compared original width during installation of the Sika® floor Joint panel. Don't ceed the maximum positive joint movement capacity, otherwise the teeth of the Sika® floor Joint panel will become unsupported and mardamaged. 3. Negative joint movement is the amount the gap can close, compared its original width during installation of the Sika® floor Joint panel. Note: The sealant may break at a positive joint movement of approx. 15–20 mm, however this does not affect the technical performance of Sika® FloorJoint EX. The purpose of the joint sealant is the reduction of pick-up in the joint, not to provide water tightness. Install Sikadur® Combiflex® SG System below Sika® FloorJoint EX if a waterproof joint design required.						
Compressive Strength ~80 N/mm² (after 14 days at 23 °C / 50 % r.h) (DIN EN 19 Reaction to Fire Bfl s1 (composite material of panel) (EN 1330 Chemical Resistance Resistant to many chemicals. Contact Sika Technical Services for specific formation. Opening Size For gaps in the substrate with a maximum width of 50 mm. Maximal ho zontal positive joint movement = 20 mm Max. gap width1 Positive joint movement2 Max. gap width1 Positive joint movement3 -10 mm 1. Width of the gap in the concrete below Sika® floor Joint panel during stallation. 2. Positive joint movement is the amount the gap can open, compared original width during installation of the Sika® floor Joint panel. Don't ceed the maximum positive joint movement capacity, otherwise the teeth of the Sika® floor Joint panel will become unsupported and may damaged. 3. Negative joint movement is the amount the gap can close, compared its original width during installation of the Sika® floor Joint panel. Note: The sealant may break at a positive joint movement of approx. 15–20 mm, however this does not affect the technical performance of Sika® FloorJoint EX. The purpose of the joint sealant is the reduction of pick-up in the joint, not to provide water tightness. Install Sikadur® Combiflex® SG System below Sika® FloorJoint EX if a waterproof joint design required.		Height 20 mm				
Reaction to Fire Bfl s1 (composite material of panel) Resistance Resistant to many chemicals. Contact Sika Technical Services for specific formation. Opening Size For gaps in the substrate with a maximum width of 50 mm. Maximal ho zontal positive joint movement = 20 mm Max. gap width1 Positive joint movement3 50 mm 1. Width of the gap in the concrete below Sika® floor Joint panel during stallation. 2. Positive joint movement is the amount the gap can open, compared to original width during installation of the Sika® floor Joint panel. Don't ceed the maximum positive joint movement capacity, otherwise the teeth of the Sika® floor Joint panel will become unsupported and mark damaged. 3. Negative joint movement is the amount the gap can close, compared its original width during installation of the Sika® floor Joint panel. Note: The sealant may break at a positive joint movement of approx. 15–20 mm, however this does not affect the technical performance of Sika® FloorJoint EX. The purpose of the joint sealant is the reduction of pick-up in the joint, not to provide water tightness. Install Sikadur® Combiflex® SG System below Sika® FloorJoint EX if a waterproof joint design required. SYSTEMS	TECHNICAL INFORMATION					
Resistant to many chemicals. Contact Sika Technical Services for specific formation. Por gaps in the substrate with a maximum width of 50 mm. Maximal ho zontal positive joint movement = 20 mm Max. gap width1 Positive joint movement3 Max. gap width1 Positive joint movement3 1. Width of the gap in the concrete below Sika® floor Joint panel during stallation. 2. Positive joint movement is the amount the gap can open, compared original width during installation of the Sika® floor Joint panel. Don't ceed the maximum positive joint movement capacity, otherwise the teeth of the Sika® floor Joint panel will become unsupported and mar damaged. 3. Negative joint movement is the amount the gap can close, compared its original width during installation of the Sika® floor Joint panel. Note: The sealant may break at a positive joint movement of approx. 15–20 mm, however this does not affect the technical performance of Sika® FloorJoint EX. The purpose of the joint sealant is the reduction of pick-up in the joint, not to provide water tightness. Install Sikadur® Combiflex® SG System below Sika® FloorJoint EX if a waterproof joint design required. SYSTEMS	Compressive Strength	~80 N/mm² (after 14 days at 23 °C / 50 % r.h) (DIN EN 196-1				
formation. For gaps in the substrate with a maximum width of 50 mm. Maximal ho zontal positive joint movement = 20 mm Max. gap width1 Positive joint movement3 50 mm 1. Width of the gap in the concrete below Sika® floor Joint panel during stallation. 2. Positive joint movement is the amount the gap can open, compared original width during installation of the Sika® floor Joint panel. Don't ceed the maximum positive joint movement capacity, otherwise the teeth of the Sika® floor Joint panel will become unsupported and mardamaged. 3. Negative joint movement is the amount the gap can close, compared its original width during installation of the Sika® floor Joint panel. Note: The sealant may break at a positive joint movement of approx. 15–20 mm, however this does not affect the technical performance of Sika® FloorJoint EX. The purpose of the joint sealant is the reduction of pick-up in the joint, not to provide water tightness. Install Sikadur® Combiflex® SG System below Sika® FloorJoint EX if a waterproof joint design required. SYSTEMS	Reaction to Fire	Bfl s1 (composite material of panel) (EN 13301-		(EN 13301-1)		
Joint Design Max. gap width1 Positive joint movement3 50 mm +20 mm 1. Width of the gap in the concrete below Sika® floor Joint panel during stallation. 2. Positive joint movement is the amount the gap can open, compared original width during installation of the Sika® floor Joint panel. Don't ceed the maximum positive joint movement capacity, otherwise the teeth of the Sika® floor Joint panel will become unsupported and mardamaged. 3. Negative joint movement is the amount the gap can close, compared its original width during installation of the Sika® floor Joint panel. Note: The sealant may break at a positive joint movement of approx. 15–20 mm, however this does not affect the technical performance of Sika® FloorJoint EX. The purpose of the joint sealant is the reduction of pick-up in the joint, not to provide water tightness. Install Sikadur® Combiflex® SG System below Sika® FloorJoint EX if a waterproof joint design required.	Chemical Resistance	Resistant to many chemicals. Contact Sika Technical Services for specific information.				
ment2 — 10 mm 1. Width of the gap in the concrete below Sika® floor Joint panel during stallation. 2. Positive joint movement is the amount the gap can open, compared original width during installation of the Sika® floor Joint panel. Don't ceed the maximum positive joint movement capacity, otherwise the teeth of the Sika® floor Joint panel will become unsupported and mardamaged. 3. Negative joint movement is the amount the gap can close, compared its original width during installation of the Sika® floor Joint panel. Note: The sealant may break at a positive joint movement of approx. 15–20 mm, however this does not affect the technical performance of Sika® FloorJoint EX. The purpose of the joint sealant is the reduction of pick-up in the joint, not to provide water tightness. Install Sikadur® Combiflex® SG System below Sika® FloorJoint EX if a waterproof joint design required. SYSTEMS	Opening Size	For gaps in the substrate with a maximum width of 50 mm. Maximal horizontal positive joint movement = 20 mm				
 Width of the gap in the concrete below Sika® floor Joint panel during stallation. Positive joint movement is the amount the gap can open, compared original width during installation of the Sika® floor Joint panel. Don't ceed the maximum positive joint movement capacity, otherwise the teeth of the Sika® floor Joint panel will become unsupported and mardamaged. Negative joint movement is the amount the gap can close, compared its original width during installation of the Sika® floor Joint panel. Note: The sealant may break at a positive joint movement of approx. 15–20 mm, however this does not affect the technical performance of Sika® FloorJoint EX. The purpose of the joint sealant is the reduction of pick-up in the joint, not to provide water tightness. Install Sikadur® Combiflex® SG System below Sika® FloorJoint EX if a waterproof joint design required. 	Joint Design	Max. gap width1		Negative joint move- ment3		
stallation. 2. Positive joint movement is the amount the gap can open, compared original width during installation of the Sika® floor Joint panel. Don't ceed the maximum positive joint movement capacity, otherwise the teeth of the Sika® floor Joint panel will become unsupported and madamaged. 3. Negative joint movement is the amount the gap can close, compared its original width during installation of the Sika® floor Joint panel. Note: The sealant may break at a positive joint movement of approx. 15–20 mm, however this does not affect the technical performance of Sika® FloorJoint EX. The purpose of the joint sealant is the reduction of pick-up in the joint, not to provide water tightness. Install Sikadur® Combiflex® SG System below Sika® FloorJoint EX if a waterproof joint design required.		50 mm	+20 mm	-10 mm		
		 Positive joint movement is the amount the gap can open, compared to its original width during installation of the Sika® floor Joint panel. Don't exceed the maximum positive joint movement capacity, otherwise the teeth of the Sika® floor Joint panel will become unsupported and may be damaged. Negative joint movement is the amount the gap can close, compared to its original width during installation of the Sika® floor Joint panel. Note: The sealant may break at a positive joint movement of approx. 15–20 mm, however this does not affect the technical performance of Sika® FloorJoint EX. The purpose of the joint sealant is the reduction of dirt pick-up in the joint, not to provide water tightness. Install Sikadur® Combiflex® SG System below Sika® FloorJoint EX if a waterproof joint design is 				
Systems • Sika® Floor Joint PB-30 EX - Floor joint panel for standard application	SYSTEMS					
	Systems	Sika® Floor Joint PB-30 EX - Floor joint panel for standard application				

APPLICATION INFORMATION

Consumption 1 piece per 1,2 linear metres of joint

APPLICATION INSTRUCTIONS

APPLICATION

Reference must be made to further documentation where applicable, such as relevant method statement, application manual and installation or working instructions. Refer to the Sika Method Statement: Sika® FloorJoint EX

FURTHER INFORMATION

- Sika Method Statement: Evaluation and preparation of surfaces for flooring Systems
- Sika Method Statement: Sika® FloorJoint EX
- System Data Sheet: Sika® FloorJoint PB-30 EX



IMPORTANT CONSIDERATIONS

- The product must only be applied in accordance with its intended use.
- For outdoor use only if the traffic speed is limited to < 30 km/h (<19 mph) and if the polymer panel is coated with UV protection.
- Never remove the masking tape affixed to the bottom side of the Sika® FloorJoint EX panels. The masking tape is necessary to keep the two composite parts of the panel separate, allowing the movement of the joint after installation.
- No relative vertical displacement of the concrete slabs can occur along the length of either side of the joint. Where necessary, apply appropriate measures such as anchoring/bolting or ground consolidation by injection prior to installation of the Sika® floor Joint panel.
- Do not exceed the maximum positive joint movement capacity, otherwise the teeth of the panels become unsupported and may break.
- Settlement of the substrate or adhesive can result in cracks in Sika® FloorJoint EX. These cracks do not constitute a defect since they don't affect the viability and suitability for use.
- Do not exceed the maximum grinding depth of 2 mm. If the maximum grinding depth of 2 mm has been exceeded the mechanical resistance of the profile is reduced. Replace the panel if the maximum grinding depth has been exceeded.
- Periodically inspect the rubber seal and renew if necessary.
- Continuously monitor the abrasion of the diamond cutting disk used for preparing the cut-out. Regularly readjust the disk to ensure all cuts are prepared with a constant depth.
- Do not use a hammer for placing and adjusting the floor panel during installation.
- The joint profile must be placed offset (eccentrically) 85 mm from the edge of the existing gap in the concrete.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

Sika Danmark A/S

Hirsemarken 5 3520 Farum Tlf. +45 48 18 85 85 www.sika.dk







PRODUCT DATA SHEET Sika® FloorJoint EX April 2020, Version 03.01 020816140020000005

ECOLOGY, HEALTH AND SAFETY

REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in this product data sheet.Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0.1 % (w/w)

LEGAL NOTES

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

SikaFloorJointEX-en-DK-(04-2020)-3-1.pdf

