

## PRODUCT DATA SHEET

# Sikafloor®-3000 Snapbooster

Polyurethane resin accelerator

### DESCRIPTION

Sikafloor®-3000 Snapbooster is a liquid, which is added to Sikafloor®-3000 or Sikafloor®-3000 FX to accelerate the curing process, while maintaining the full pot life of the accelerated products.

### USES

The product can be used as a curing accelerator for fast track flooring applications in new buildings and in maintenance and refurbishment applications.

### CHARACTERISTICS / ADVANTAGES

- Easy to add and mix into Sikafloor® Polyurethane resin

### PRODUCT INFORMATION

<b>Composition</b>	Tin catalyst and thiol component	
<b>Packaging</b>	Box of 12 × 280 g bottles	
<b>Shelf life</b>	12 months from date of production	
<b>Storage conditions</b>	The Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Protect the Product from direct sunlight. Always refer to packaging.	
<b>Density</b>	~1 kg/l	(EN ISO 2811-1)

### APPLICATION INFORMATION

<b>Mixing ratio</b>	Add 280 g (1 bottle) for 20 kg of mixed Sikafloor®-3000 or Sikafloor®-3000 FX	
<b>Ambient air temperature</b>	Minimum	+15 °C
	Maximum	+30 °C
<b>Substrate temperature</b>	Minimum	+15 °C
	Maximum	+30 °C
<b>Pot Life</b>	Note: The addition of the Product does not affect the pot life of the mixed coating.	
<b>Waiting time to overcoating</b>	When Sikafloor®-3000 Snapbooster is added to Sikafloor®-3000 or Sikafloor®-3000 FX:	

Temperature	Minimum waiting time
+15 °C	4 hours
+20 °C	3 hours
+25 °C	2 hours

Note: Times are approximate and will be affected by changing ambient conditions, particularly temperature and relative humidity.

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER INFORMATION

- Product Data Sheets: Sikafloor®-3000, Sikafloor®-3000 FX

## ECOLOGY, HEALTH AND SAFETY

## APPLICATION INSTRUCTIONS

### MIXING

#### IMPORTANT

##### Excessive amounts of booster

Excessive amounts of booster will affect the performance negatively and may lead to softness and stickiness in the final cured product.

1. Follow the mixing ratio as described in Application Information.

#### IMPORTANT

##### Application below application temperature

Using the product at temperatures lower than specified in the Application Information will not reduce the curing time of the final product to less than 24 hours.

##### Note: Insufficient amounts of booster

Insufficient amounts of booster will increase the curing time of the final product.

1. Follow the mixing ratio as described in Application Information.

### Mixing procedure

Note: Sikafloor®-3000 Snapbooster is added to Sikafloor®-3000 or Sikafloor®-3000 FX on site as part of the mixing process.

- The A and B parts of Sikafloor®-3000 or Sikafloor®-3000 FX have been mixed completely as described in the respective Product Data sheet.
1. Before adding the Product, mix the resins for approximately 40 seconds.
  2. Gradually add Sikafloor®-3000 Snapbooster to the mixture.
  3. Mix for a further 2 minutes until a uniform mix is achieved.
  4. To ensure thorough mixing, pour materials into another container and mix for an additional minute to achieve a smooth and uniform mix.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

## LEGAL NOTES

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

Sika Danmark A/S  
Hirsemarken 5  
3520 Farum  
Tlf. +45 48 18 85 85  
www.sika.dk



PRODUCT DATA SHEET  
Sikafloor®-3000 Snapbooster  
December 2022, Version 01.01  
020816220010000028

Sikafloor-3000Snapbooster-en-DK-(12-2022)-1-1.pdf