

PRODUCT DATA SHEET

SikaFast®-555 L10

Fast curing, 2-component structural adhesive

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Properties	SikaFast®-555 L10 (A)	SikaFast®-555 (B)
Chemical base	Acrylate	
Color (CQP001-1)	White	Grey
mixed	Grey	
Cure mechanism	Radical polymerization	
Density	1.13 kg/l	1.50 kg/l
mixed (calculated)	1.16 kg/l	
Mixing ratio	by volume 10 : 1	
	by weight 10 : 1.3	
Consistency	Thixotropic paste	
Application temperature	5 – 40 °C	
Open time (CQP526-2)	10 minutes ^A	
Fixing time	time to reach 80 % of torsional strength 25 minutes ^A	
Shore D hardness (CQP023-1 / ISO 48-4)	50 ^{A, B}	
Tensile strength (CQP036-1 / ISO 527)	11 MPa ^{A, B}	
Elongation at break (CQP036-1 / ISO 527)	200 % ^{A, B}	
Tensile lap-shear strength (CQP046-6 / ISO 4587)	12 MPa ^{A, B, C}	
Service temperature (CQP513-1)	-40 – 80 °C	
Shelf life (CQP016-1)	12 months ^D	

CQP = Corporate Quality Procedure

^C) Adhesive layer: 25 x 12.5 x 1.5 mm / on aluminum^A) 23 °C / 50 % r. h.^D) Stored below 25 °C and protected from direct sun light^B) Cured for 1 week at 23 °C

DESCRIPTION

SikaFast®-555 L10 is an acrylic based, fast curing, flexibilized structural, 2-component adhesive. It has a pasty-like consistency allowing for vertical and horizontal, easy and precise application. It is suitable to replace mechanical fixation and provides very good adhesion on various substrates such as metals, plastics, glass and wood.

This product is available with different pot life versions to adapt to specific application requirements.

PRODUCT BENEFITS

- Strength development within minutes after application
- Adhesion to a wide range of substrates without or with limited surface preparation
- High strength and impact resistance
- Solvent and acid free
- Lower odor than products containing MMA

AREAS OF APPLICATION

SikaFast®-555 L10 is designed for fast bonding and can replace mechanical fixations such as rivets, screws or welding. It is suitable for high strength fastening of concealed joints and exhibits excellent adhesion on different types of substrates including metals, plastics, glass, wood, etc.

This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.

CURE MECHANISM

SikaFast®-555 L10 cures according to radical chain polymerization. Open and fixture time are influenced by mixing ratio deviations as well as temperature. The higher the temperatures, the shorter the open and fixture times are and vice versa.

CHEMICAL RESISTANCE

In the view of potential chemical or thermal exposure, it is required to conduct a project related testing.

METHOD OF APPLICATION

Surface preparation

Surfaces must be clean, dry and free from grease, oil and dust. Remove all loose particles or residues by cleaning it thoroughly. For best adhesion performance on non-porous substrates pre-treat the bonding area with Sika® ADPrep prior to the bonding process. Due to the diversity of materials, preliminary tests with original substrates are necessary.

Application

SikaFast®-555 L10 is applied with a mixing ratio of 10:1 by volume from cartridges or bulk packaging. Consider that if applied in large masses, heat is generated by the exothermic reaction. To avoid excessive temperature increase, bond line thickness is limited to 3 mm, but must measure at least 0.5 mm. Optimum temperature for the bonding process is between 15 °C and 25 °C. The approved temperature range for substrates and adhesive is between 5 °C and 40 °C. The influence of the reactivity by temperature changes has to be respected.

After the open time has elapsed the bonded parts must not be moved against each other anymore. When the fixture time is reached the parts can be moved provided that no additional stress is distributed to the bond line. SikaFast®-555 L10 can be processed with pneumatic driven piston guns as well as pump equipment. For advice on selecting and setting up a suitable pump system, contact the System Engineering Department of Sika Industry.

Removal

Uncured excess of SikaFast®-555 L10 can be removed easily before curing with a dry wipe, with Sika® Remover-208 or another suitable solvent. Once the adhesive is cured it can only be removed mechanically. Hands and exposed skin shall be washed immediately using Sika® Cleaner-350H towels or a suitable industrial hand cleaner and water. Do not use solvents on skin.

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry. Copies of the following publications are available on request:

- Safety Data Sheets
- ATI: Mixer alternatives for cartridges

PACKAGING INFORMATION

SikaFast®-555 L10 (A+B)

Dual cartridge	250 ml
Mixer: Sulzer MixPac™ MFQX 07-24T	

Dual cartridge	490 ml
Mixer: Sulzer MixPac™ MFHX 10-24T	

SikaFast®-555 L10 (A)

Pail	20 l
------	------

SikaFast®-555 (B)

Pail	18 l
------	------

Please contact customer service for which packaging sizes are available in Denmark.

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

DISCLAIMER

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

PRODUCT DATA SHEET

SikaFast®-555 L10
Version 06.01 (12 - 2025), en_DK
01290555550001020

