

PRODUCT DATA SHEET

Sarnacol® T-660

Adhesive for Sarnafil® TG 66, Sarnafil® TS 77 roof waterproofing membranes and Sarnafil® sub-roof membranes

DESCRIPTION

Butyl rubber based one-pack contact adhesive

USES

Sarnacol® T-660 is a contact adhesive to bond Sarnafil® TG 66-type, Sarnafil® TS 77-type and Sarnafil® TU-type membranes in perimeter and flashing areas.

CHARACTERISTICS / ADVANTAGES

Adheres to solid, rough and clean surfaces

APPROVALS / CERTIFICATES

Quality management system EN ISO 9001/14001

PRODUCT INFORMATION

Composition	Butyl rubber-based solvent-containing one-pack contact adhesive	
Packaging	One way container	18kg, 5kg
	Packing unit	Europallet or single container
Please contact our customer service, for information of what packaging sizes are sold in Denmark.		
Appearance / Colour	Yellow	
Shelf life	15 months from date of production if stored properly in original, unopened and undamaged sealed container. Expiry date on container.	
Storage conditions	Store in dry conditions at temperatures between +5 °C to +30 °C	
Density	~0,79 kg/l (+20 °C)	
Volatile organic compound (VOC) content	VOC-CH: 67,7 %	
	VOC-EU: 67,7 %	
Consistency	Liquid	

APPLICATION INFORMATION

Consumption	Consumption depends on the roughness and absorbency of the substrate and ranges from 300–500 g/m ² on closed substrates to 1000 g/m ² on very absorbent substrates.
Ambient air temperature	Temperature limits for the installation of the adhesive: At least +5 °C
Substrate temperature	Temperature limits for the installation of the adhesive: At least +5 °C

Substrates

- Concrete, lightweight concrete, brick, plaster
- Oriented strands fibre (OSB) boards, plywood panels
- Fibre cement boards
- Aged bitumen
- Mineral fibre boards with sufficient compressive strengths and appropriate surface for bonding
- PUR/PIR insulation boards with lamination (glass or mineral fibre fleece and coated aluminium)
- Polyester (thermal activation required), hard PVC
- Galvanized steel, aluminium, nickel chromium steel

Setting time

The strength required for the intended stress is achieved immediately. Final strength is achieved after approx. 1 week and depends on the temperature and humidity.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

The substrate must offer sufficient strength and adhesion to resist the forces generated by wind suction.

SUBSTRATE PREPARATION

The substrate must be resistant to solvent, firm, clean, dry, free of stripping agents and free of oil and grease. Sheet metal must be cleaned with Solvent T 660 before adhesive is applied.

APPLICATION

Application Guideline

Based on the valid installation instructions of the relevant roof waterproofing membrane.

General Information

Sarnacol® T-660 must be stirred well and carefully before use. Close the container if work is stopped for a long period. Sarnacol® T-660 can be diluted with Solvent T 660 to adjust fluidity. Use Solvent T 660 to remove adhesive residues on the roof membrane.

General principles for bonding (contact bonding)

The adhesive is spread evenly to the substrate, preferably using a roller. Do not apply the adhesive to an area greater than can be covered in one day. Allow the adhesive to dry completely. The minimum evaporation time is 2 hours, the maximum 10 hours. Apply two coats of adhesive on absorbent substrates (the first coat must have dried out completely before the second is applied). Apply the adhesive evenly on the underside of the roof membrane, preferably using a roller (welding seam overlap area must be free of adhesive). Once the adhesive has been allowed to evaporate sufficiently (finger test after approx. 30 minutes), position the roof membrane, straighten it, bond it and press it down well with a roller. The time to be allowed for evaporation depends on the temperature, air humidity, condition of the substrate and quantity of adhesive.

Heat activation

After bonding, the adhesion is generally improved by warming up the roof membrane. Therefore the roof membrane is heated externally by means of a heat source (Sarnafil® heat gun) and pressed down immediately using a roller. Avoid any glossing on the roof membrane, particularly in the area of the welding seam overlap.

CLEANING OF EQUIPMENT

Tools and equipment must be cleaned with Solvent T 660 immediately after use.

IMPORTANT CONSIDERATIONS

Unsuitable substrates:

- EPS/XPS insulation boards
- Copper plate

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

PRODUCT DATA SHEET

Sarnacol® T-660

October 2020, Version 02.01
02094507200000002

LEGAL NOTES

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

Sika Danmark A/S

Hirsemarken 5
3520 Farum
Tlf. +45 48 18 85 85
www.sika.dk



PRODUCT DATA SHEET

Sarnacol® T-660

October 2020, Version 02.01
020945072000000002

SarnacolT-660-en-DK-(10-2020)-2-1.pdf