

PRODUCT DATA SHEET

Sikaplan® WP 1100-20 HL

2.0 mm thick PVC sheet waterproofing membrane for basements and tunnels

DESCRIPTION

Sikaplan® WP 1100-20 HL is a flexible, 2,0 mm thick, homogeneous sheet waterproofing membrane. It contains a signal layer and is based on high-quality polyvinylchloride (PVC-p).

USES

The Product is designed for:

- Waterproofing of basements against water ingress
- Waterproofing of tunnels against water ingress

CHARACTERISTICS / ADVANTAGES

- Part of the complete waterproofing membrane system
- Proven performance over decades
- Contains no recycled materials and no DEHP (DOP) plasticisers

- High resistance to ageing
- Good resistance to microbial degradation
- Good resistance to root penetration
- Suitable for contact with acidic (soft) water and alkaline environments
- Optimised flexibility, tensile strength and multi-axial elongation
- Optimised workability and thermally weldable

APPROVALS / CERTIFICATES

- CE Marking and Declaration of Performance to EN 13491 - Geosynthetic barriers — Characteristics required for use as a fluid barrier in the construction of tunnels and underground structures
- CE Marking and Declaration of Performance to EN 13967 — Flexible sheets for waterproofing - Damp proofing and basement tanking

PRODUCT INFORMATION

Composition	PVC-p	
Packaging	Roll width	2.2 m
	Roll length	20 m or specified
Shelf life	5 years from date of production	
Storage conditions	The Product must be stored in original unopened and undamaged sealed packaging in dry conditions and temperatures between +5 °C and +35 °C. Protect the Product from direct weather exposure. Store in a horizontal position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging.	
Appearance and colour	Surface texture	smooth
	Signal layer colour	yellow
	Bottom layer colour	black
Effective thickness	2.0 mm (-0.1 mm / +0.2 mm)	(EN 1849-2)

SYSTEM INFORMATION

System structure

Ancillary products:

- Sika® FlexoDrain
- Sikaplan® Geotextiles
- Sika® Drains
- Sika® W Tundrains
- Sikaplan® WP Drainage Angles
- Sikaplan® WP Disc
- Sika® Waterbars WP
- Sikaplan® WP Tape
- Sikaplan® WP Control Sockets
- Sikaplan®-8 Separation
- Sikaplan® WP Trumpet Flange
- Sika® Anchors
- Sikaplan® WP Protection Sheets

TECHNICAL INFORMATION

Resistance to impact	Method A, 500 g falling weight	Watertight at 1000 mm drop height	(EN 12691)
Resistance to static loading	No perforation at 20 kg for 24 h		(EN 12730)
Resistance to static puncture	2.35 kN ± 0.25 kN		(EN ISO 12236)
Tensile strength	Longitudinal (MD)	17 N/mm ² ± 2 N/mm ²	(EN ISO 527-3)
	Transversal (CMD)	16 N/mm ² ± 2 N/mm ²	
	Longitudinal (MD)	17 N/mm ² ± 2 N/mm ²	(EN 12311-2)
	Transversal (CMD)	16 N/mm ² ± 2 N/mm ²	
Tensile strain at break	Longitudinal (MD)	> 300 %	(EN ISO 527-3)
	Transversal (CMD)	> 300 %	
Burst strength	D = 1.0 m	≥ 80 %	(EN 14151)
Joint shear resistance	> 950 N/50mm		(EN 12317-2)
Service temperature	Minimum	-10 °C	
	Maximum	+35 °C	
Ambient maximum temperature of liquids	+35 °C		
Foldability at low temperature	No cracks at -20 °C		(EN 495-5)
Watertightness	Method B: 24 hours at 60 kPa	Pass	(EN 1928)
Permeability to liquid water	< 10 ⁻⁶ m ³ ·m ⁻² ·d ⁻¹		(EN 14150)
Chemical resistance	Change in tensile strength, 5-6 % sulphurous acid test, aged 90 days at +23 °C	< 20 %	(EN 1847)
	Foldability at low temperatures, 5-6 % sulphurous acid test, aged 90 days at +23 °C	No cracks at -20 °C	

	Change in tensile strength and elongation, saturated lime wash, aged 112 days at +50 °C	< 20 %	(EN 14415)
Behaviour after storage in warm water	Change in tensile strength, aged 360 days at +70 °C	< 20 %	(EN 14415)
	Change in elongation, aged 360 days at +70 °C	< 20 %	
	Change in mass, aged 360 days at +70 °C	< 4 %	
	Reduction of impact load, aged 360 days at +70 °C	≤ 30 %	
	Dimensional change, aged 360 days at +70 °C	< 2 %	
Resistance to oxidation	Change in tensile strength, aged 120 days at +80 °C	< 10 %	(EN 14575)
	Change in elongation, aged 120 days at +80 °C	< 10 %	
Microbiological resistance	Change in tensile strength, aged 16 weeks	< 15 %	(EN 12225)
	Change in elongation, aged 16 weeks	< 15 %	
Durability of watertightness against chemicals	Calcium hydroxide, aged 28 days at +23 °C, tested 24 hours at 60 kPa	Pass	(EN 1847)
Resistance to UV exposure	Not permanently UV stable		
Resistance to weathering	Not resistant to permanent weathering		
Dimensional change after heat	Longitudinal (MD), aged 6 hours at +80 °C	< 2 %	(EN 1107-2)
	Transversal (CMD), aged 6 hours at +80 °C	< 2 %	
Durability of watertightness against ageing	Aged 12 weeks at +70 °C, tested 24 hours at 60 kPa	Pass	(EN 1296)
Reaction to fire	Class E		(EN 13501-1)

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in this product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0.1 % (w/w)

APPLICATION INSTRUCTIONS

IMPORTANT

Strictly follow installation procedures

Strictly follow installation procedures as defined in Method Statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

SUBSTRATE QUALITY

For information on substrate quality / pre-treatment, refer to the following Sika® method statement:

- Sikaplan® WP sheet membrane (PVC) system for waterproofing basements and other below ground structures
- Sikaplan® WP sheet membrane (PVC) system for waterproofing tunnels

APPLICATION METHOD / TOOLS

For information on application, refer to the following Sika® method statement:

- Sikaplan® WP sheet membrane (PVC) system for waterproofing basements and other below ground structures
- Sikaplan® WP sheet membrane (PVC) system for waterproofing tunnels

IMPORTANT

Application by trained personnel

The application of this Product must only be carried out by Sika® trained and/or approved contractors, experienced in this type of application.

IMPORTANT

Ventilation in confined spaces

Always ensure good ventilation when applying the Product in a confined space.

IMPORTANT

Not resistant to bitumen and plastics

The Product is not resistant to permanent contact with bitumen and some types of plastics other than PVC.

- For use over or adjacent to these materials, apply a separation layer of polypropylene geotextile (≥ 150 g/m²).

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

Sika Danmark A/S
Hirsemarken 5
3520 Farum
Tlf. +45 48 18 85 85
www.sika.dk



PRODUCT DATA SHEET
Sikaplan® WP 1100-20 HL
January 2023, Version 05.01
020720101000000003

SikaplanWP1100-20HL-en-DK-(01-2023)-5-1.pdf