

PRODUCT DATA SHEET

SikaForce®-710 L30

Fast curing 2-component balancing material

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Properties	Component A SikaForce®-710 L35	Component B SikaForce®-050
Chemical base	Polyols	Isocyanate derivatives
Color (CQP001-1)	Beige	Brown
	mixed	Beige
Cure mechanism	Polyaddition	
Density (uncured)	1.64 g/cm ³	1.22 g/cm ³
	mixed (calculated)	1.56 g/cm ³
Mixing ratio	by volume	100 : 25
	by weight	100 : 19
Viscosity (CQP029-4)	Rheometer, PP25, shear rate 10 s ⁻¹ , d=1 mm	24 Pa·s ^A
	mixed	14 Pa·s ^A
Application temperature	10 – 40 °C	
Pot-life (CQP536-3)	30 minutes ^A	
Shore D hardness (CQP023-1 / ISO 48-4)	45 ^B	
Tensile strength (CQP543-1 / ISO 527)	6 MPa ^{B, C}	
Elongation at break (CQP543-1 / ISO 527)	22 % ^{B, C}	
Tensile lap-shear strength (CQP546-1 / ISO 4587)	7 MPa ^{B, D}	
Shelf life	drum	12 months
	cartridge	9 months

CQP = Corporate Quality Procedure

C) tested at 2 mm/min

A) 23 °C / 50 % r. h

D) adhesive layer: 25 x 12.5 x 3 mm / on GFRP

B) cured for 28 days at 23 °C / 50 % r. h

DESCRIPTION

SikaForce®-710 L30 is a 2-component polyurethane adhesive which cures at room temperature.

It is designed for balancing of wind turbine blades. The system is characterized by high injectability and thixotropic viscosity build up.

PRODUCT BENEFITS

- Room temperature curing
- High injectability
- Medium viscosity
- Easy to apply
- Solvent free

AREAS OF APPLICATION

SikaForce®-710 L30 is primarily used for balancing of wind turbine blades in factory but also for onsite-rebalancing. The material can be used in other industry applications such as bonding of sandwich panels after a detailed project review.

This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed ensuring adhesion and material compatibility.

PRODUCT DATA SHEET

SikaForce®-710 L30

Version 01.01 (08 - 2024), en_DK

012104577100001040

CURE MECHANISM

The curing of SikaForce®-710 L30 takes place by a chemical reaction of the two components. Higher temperatures speed up the curing process and lower slow it down.

CHEMICAL RESISTANCE

In case of chemical or thermal exposure, conduct project related testing.

METHOD OF APPLICATION

Product preparation

Component A must be stirred thoroughly before use.

Surface preparation

Surfaces must be clean, dry and free from grease, oil, dust and contaminants. After the cleaning process, a physical or chemical pretreatment might be required, depending on surface and type of material. The type of pretreatment must be determined by tests.

Mixing process

The procedure for manual application is as follows: Ensure that the A-component is stirred thoroughly to avoid any sediment or separation, taking care not to stir too vigorously as this may introduce air into the product. Add the B-component in the specified ratio and stir thoroughly, ensuring a homogeneous mixture is achieved.

Application

Apply before reaching half of the pot-life and join parts together within the open time. Consider that, if mixed in larger amounts, the exothermic reaction can reduce the pot-life and open time significantly.

SikaForce®-710 L30 can be applied with automated application equipments. For automated applications, contact the System Engineering Department of Sika Industry.

Removal

Uncured SikaForce®-710 L30 may be removed from tools and equipment with SikaForce®-7260 Cleaner. Once cured, the material can only be removed mechanically.

Hands and exposed skin have to be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water.

Do not use solvents on skin.

STORAGE CONDITIONS

SikaForce®-710 L30 has to be kept between 10 °C and 30 °C in a dry place. Do not expose it to direct sunlight or frost. After opening of the packaging, the content has to be protected against humidity.

The lowest allowed temperature during transportation is -20 °C for max. 7 days.

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets

PACKAGING INFORMATION

SikaForce®-710 L35 (A)

Pail	25 kg
Drum	300 kg
Container	1 500 kg

SikaForce®-050 (B)

Can	0.45 kg
	1 kg
	5 kg
	20 kg
Pail	25 kg
Drum	250 kg

SikaForce®-710 L30 (A+B)

Dual cartridge	415 ml
Mixer: MFHX 10-32 by medmix	
Mixer: MFHX 10-24 by medmix	

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

DISCLAIMER

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

PRODUCT DATA SHEET

SikaForce®-710 L30

Version 01.01 (08 - 2024), en_DK
012104577100001040

