

## PRODUCT DATA SHEET

# Sikafloor®-329

(formerly MTop BC 329)

Elastic polyurethane floor coating

### DESCRIPTION

Sikafloor®-329 is a 2-part, solvent-free, elastic, self-levelling polyurethane base coat resin. It provides acoustic insulation to reduce footfall sound.

### USES

Sikafloor®-329 is used as an elastic, self-smoothing base layer for Sika ComfortFloor® systems.

Please note:

- The Product may only be used by experienced professionals.
- The Product may only be used for interior applications.

### FEATURES

- Reduces footfall sound and contact noise
- Soft underfoot
- Good crack bridging ability
- Good mechanical resistance
- High elasticity
- Very low VOC emissions

### PRODUCT INFORMATION

<b>Composition</b>	Polyurethane		
<b>Packaging</b>	Container Part A	10.4 kg	
	Container Part B	4.6 kg	
	Container Part A + Part B	15.0 kg	
Refer to the current price list for available packaging variations.			
<b>Appearance and colour</b>	Part A	coloured	
	Part B	light brown, transparent	
	Cured colour	grey	
<b>Shelf life</b>	12 months from date of production		
<b>Storage conditions</b>	The Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to the packaging. Refer to the current Safety Data Sheet for information on safe handling and storage.		
<b>Density</b>	Part A	0.85 kg/l	(EN ISO 2811-1)
	Part B	1.11 kg/l	
	Mixed Product	0.93 kg/l	

#### PRODUCT DATA SHEET

Sikafloor®-329

February 2025, Version 03.01

02081200000002005

Solid content by mass	100 %
Solid content by volume	100 %

## TECHNICAL INFORMATION

Shore A hardness	Cured 7 days at +23 °C	63	(EN ISO 868)
Tensile strength	Cured 7 days at +23 °C and 50 % r.h.	1.7 MPa	(DIN 53504)
Tensile strain at break	Cured 7 days at +23 °C	80 %	(DIN 53504)
Tensile adhesion strength	> 1.5 N/mm <sup>2</sup> (failure in concrete)		(EN 1542)
Sound insulation	Refer to the individual System Data Sheet.		

## APPLICATION INFORMATION

Mixing ratio	Part A : Part B (by weight)	100 : 44	
Consumption	Unfilled	2.5 kg/m <sup>2</sup>	
Material temperature	Maximum	+30 °C	
	Minimum	+10 °C	
Ambient air temperature	Maximum	+30 °C	
	Minimum	+10 °C	
Relative air humidity	Maximum	75 % r.h.	
Dew point	Beware of condensation. The substrate and uncured applied product must be at least +3 °C above dew point to reduce the risk of condensation on the surface of the applied product.		
Substrate temperature	Maximum	+30 °C	
	Minimum	+10 °C	
Substrate moisture content	<b>Substrate</b>	<b>Test method</b>	<b>Moisture content</b>
	Cementitious substrates	Calcium carbide method (CM method)	≤ 4 %
	No rising moisture (ASTM D4263, polyethylene sheet)		
Pot Life	+20 °C	25 minutes	
Waiting time to overcoating	Before overcoating the Product, allow:		
	<b>Temperature</b>	<b>Minimum</b>	<b>Maximum</b>
	+15 °C	~24 hours	~3 days
	+20 °C	~12 hours	~48 hours
	+30 °C	~8 hours	~36 hours
	Note: Times are approximate and will be affected by changing ambient conditions, particularly temperature and relative humidity.		

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER DOCUMENTATION

Refer to the following method statements:

- Sika Method Statement — Evaluation and preparation of surfaces for flooring systems
- Sika Method Statement — Sikafloor® mixing and application

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

### Regulation (EC) No 1907/2006 (REACH) - Mandatory training

As from 24 August 2023 adequate training is required before industrial or professional use of this product. For more information and a link to the training visit [www.sika.com/pu-training](http://www.sika.com/pu-training).



## APPLICATION INSTRUCTIONS

### EQUIPMENT

#### MIXING EQUIPMENT

- Electric double-paddle mixer (> 700 W, 300 rpm to 400 rpm)

#### APPLICATION EQUIPMENT

- Pin leveller
- Trowels, including serrated
- Spiked roller

### SUBSTRATE QUALITY

#### IMPORTANT

#### Reduced service life due to incorrect treatment of cracks

The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.

1. For static cracks, ensure the width is suitable for overcoating with Sikafloor®-329.
2. For dynamic cracks, ensure the movement is within the movement capacity of Sikafloor®-329.

#### TREATMENT OF JOINTS AND CRACKS

Construction joints and existing static surface cracks in substrate require pre-treating before full layer application. Use Sikadur® or Sikafloor® resins.

#### SUBSTRATE CONDITION

Cementitious substrates must be structurally sound and of sufficient compressive strength (minimum 25 N/mm<sup>2</sup>) with a minimum tensile strength of 1.5 N/mm<sup>2</sup>.

Substrates must be clean, dry and free of contaminants such as dirt, oil, grease, coatings, laitance, surface treatments and loose friable material.

#### Maximum slope gradient

Note: Do not apply on substrates with a slope > 1 % gradient.

### SUBSTRATE PREPARATION

### MECHANICAL SUBSTRATE PREPARATION IMPORTANT

#### Surface defects due to voids in the substrate

Voids and blow holes in the substrate will weaken the surface and damage the covering Product if not repaired during the preparation process.

1. Fully expose blow holes and voids during surface preparation to identify the required repairs.
1. Remove weak cementitious substrates.
2. Prepare cementitious substrates mechanically using abrasive blast cleaning, abrasive planing or scarifying equipment to remove cement laitance.
3. Before applying thin layer resins, remove high spots by grinding.
4. Before applying the Product, remove all dust, loose and friable material from the application surface with an industrial vacuuming equipment.
5. Level the surface or fill cracks, blow holes and voids with products from the Sikafloor®, Sikadur® and Sikagard® range of materials.

For additional information on products for leveling and repairing defects, contact Sika® Technical Services.

### SUBSTRATE PREPARATION OF NON-CEMENTITIOUS SUBSTRATES

For information on substrate preparation of non-cementitious substrates, contact Sika® Technical Services.

### APPLICATION

#### IMPORTANT

#### Strictly follow installation procedures

Strictly follow installation procedures as defined in Method Statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

#### IMPORTANT

#### Protect from moisture

After application, protect the Product from damp, condensation and direct water contact for at least 24 hours.

#### IMPORTANT

#### Foaming due to water contact of uncured material

Uncured material reacts with water of any kind, which leads to foaming.

1. During the application, wear head and wrist bands to avoid sweat falling onto the uncured material.

#### IMPORTANT

#### No application on rising moisture

Do not apply on substrates with rising moisture.

#### IMPORTANT

#### Damaged finish due to heating with fossil fuel heaters

Fossil fuel heaters powered by gas, oil or paraffin produce large quantities of both carbon dioxide and water vapour, which may adversely affect the finish.

1. For temporary heating, use only electrically powered warm air blower systems. Do not use gas, oil, paraffin or other fossil fuel heaters.

#### PRODUCT DATA SHEET

Sikafloor®-329

February 2025, Version 03.01

02081200000002005

## IMPORTANT

### Indentations in resin due to high temperature combined with high point loading

Under certain conditions, underfloor heating or high ambient temperatures combined with high point loading may lead to indentations in the resin.

### SELF-SMOOTHING WEARING LAYER

1. Pour the mixed Product onto the substrate. For the consumption, refer to Application Information.
2. Apply the Product evenly over the surface with a serrated trowel.
3. To achieve a smooth finish, smooth the surface with the flat side of a trowel.
4. Back roll the surface in two directions at right angles with a steel spike roller.

### CLEANING OF EQUIPMENT

Clean all tools and application equipment with Sika® Thinner C immediately after use. Hardened material can only be removed mechanically.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

## LEGAL NOTES

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

#### Sika Danmark A/S

Hirsemarken 5  
3520 Farum  
Tlf. +45 48 18 85 85  
www.sika.dk



#### PRODUCT DATA SHEET

Sikafloor®-329  
February 2025, Version 03.01  
02081200000002005

Sikafloor-329-en-DK-(02-2025)-3-1.pdf