**BUILDING TRUST** 

PRODUCT DATA SHEET

# Sikafloor® Marine-570

IMO approved self-levelling 2-component polyurethane decorative resin

# TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Properties		Sikafloor® Marine-570 (A)	Sikafloor® Marine-570 (B)
Chemical base		Polyurethane	Isocyanate
Color (CQP001-1)	nixed	Colored	Yellowish
		Various colours available	
		contact customer service DK	
Density		1.5 kg/l	1.2 kg/l
m	nixed	1.4 kg/l	
Solid content		100 %	
Mixing ratio by we	eight	79 : 21	
Application temperature substrate / clin	mate	10 – 30 °C <sup>A, B</sup>	
Working time	10 °C	30 minutes	
	20 °C	21 minutes	
;	30 °C	18 minutes	
Shore D hardness (CQP023-1 / ISO 48-4)		50	
Tensile strength (DIN 53504)		20 MPa	
Elongation at break (DIN 53504)		100 %	
Shelf life		9 months <sup>c</sup>	12 months <sup>C</sup>

CQP = Corporate Quality Procedure  $^{A)}$  Substrates must be 3 °C above the dew point

B) max. 80 % r.h. C) stored in sealed container in up-right position in a dry place between 5 and 30 °C, protected from direct sunlight

## **DESCRIPTION**

Sikafloor® Marine-570 is a 2-component, polyurethane, tough elastic, low VOC self-smoothing marine flooring resin. It is part of the Sikafloor® Marine decorative resin systems.

Sikafloor® Marine-570 has been tested according to FTP Code system and approved according the IMO Marine Equipment Directives.

# PRODUCT BENEFITS

- Good application characteristics
- IMO approved, as primary deck covering up to a max. of 2.1 kg/m²
- IMO approved, as floor covering up to a max. of 2.5 kg/m<sup>2</sup>
- Type Approval according to DNV-CP-0338
- Transport Canada approved
- Good mechanical resistance
- Very low VOC emission
- Solvent-free
- tough elastic

## **AREAS OF APPLICATION**

Sikafloor® Marine-570 can be used interior and exterior as wearing layer compound in ship and boat construction. For interior tough floor solution and exterior as a layer compound in the Sikafloor® Marine Deco Teak solutions.

This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed ensuring adhesion and material compatibility.



#### **CURE MECHANISM**

The curing of Sikafloor® Marine-570 takes place by a chemical reaction of the two components.

Higher temperatures speed up and lower temperatures slow down the curing process.

#### CHEMICAL RESISTANCE

For advice contact the Technical Department of Sika Industry.

#### METHOD OF APPLICATION

## Surface preparation

For steel decks, an anti-corrosion protection layer applied and intact as designed by the shipyard is a pre-requisite.

The surface need to be clean, free of dirt, dust, grease, oil and loose particles before application of the SikaCor® ZP Primer. The adhesion between the anti-corrosion protection layer and SikaCor® ZP Primer must be verified. Aluminum deck needs to be clean, free of dirt, dust, grease, oil and loose particles. The aluminum substrate must be sanded with 40 – 80 grit and dust free vacuum cleaned before application of SikaCor® ZP Primer (Tiecoat).

In the case of cementitious substrates, it must be ensured that the laitance layer is completely removed. This is usually achieved by grinding. All dust, loose and friable material must be completely removed by vacuum before the next application.

Repairs to the substrate, filling of cracks, holes/voids or surface levelling must be carried out first. Repair areas must be cured before applying primers.

Ensure the substrate moisture content is equal or less than 4 % (Calcium carbide method (CM-method). Apply Sikafloor®-150/-151 as a primer to obtain a closed pore free surface.

Backing substrate for prefab installations must be clean, dry and free of all contaminants such as dirt, oil, grease and loose friable material

2-C polyurethane substrates need usually to be sanded with 40-80 grit sanding paper up to diamond disc. In case the substrate is not clean, it is required to clean it before the sanding process to ensure no debris is sanded into the surface. All dust, loose and friable material must be completely removed from the surface by vacuum cleaning before next application.

For more information and other substrates refer to the Sika Pre-Treatment Chart for Sikafloor® Marine Applications.

The application area must be protected against dirt, sun light, water and draught.

#### Mixing process

Prior to mixing all components, stir part A using the electric mixing equipment.

Add part B to part A and mix continuously for 2 minutes until a uniformly mix has been obtained. To ensure thorough mixing pour materials into a clean container and mix again for at least 1 minute to achieve a smooth consistent mix.

Excessive mixing must be avoided to minimize air entrainment.

For areas with cambers or slopes (1-3%) SikaLiquid Thickener or Sika® Extender T may be added to adapt the consistency of the product.

Remark: By adapt the consistency, the de-airing properties may be affected.

#### **Application**

Sikafloor® Marine-570 is poured and spread evenly by means of a suitable trowel or pin leveller. A spike roller may be used to improve levelling and de-airing.

For liquid application on cambers and slopes multiple applications steps might be needed. A seamless finish can be achieved when a "wet" edge is maintained during application.

#### Curing

Indications regarding curing details see table below

Tempera- ture	Walk- and overcoatable	Full loading
10 °C	24 hours	7 days
20 °C	18 hours	7 days
30 °C	12 hours	7 days

#### Removal

Uncured Sikafloor® Marine-570 can be removed from tools and equipment with Sika® Colma Cleaner or another suitable solvent. Once cured, the material can only be removed mechanically.

Hands and exposed skin shall be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water.

Do not use solvents on skin.

## **Application limits**

Beware of condensation. The substrate and uncured applied product must be at least 3 °C above dew point to reduce the risk of condensation.

Sikafloor® Marine-570 used for Sikafloor® Marine teak deck system is only available in specific colors.

Freshly applied Sikafloor® Marine-570 must be protected from damp, condensation and water for at least 1 day. Uncured material reacts in contact with water (foaming).

For consistent color matching, ensure the product in each area is applied from the same batch numbers.

For air heating use only electric powered warm air blower systems.

If Sikafloor® Marine-570 is used in interior areas and exposed to UV light, the floor must be protected by a pigmented sealer, such as Sikafloor® Marine-505.

# STORAGE CONDITIONS

The product must be stored in original, unopened and undamaged packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging. After opening of the packaging, the contents need to be protected against moisture.

#### **FURTHER INFORMATION**

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheet
- Sika Pre-Treatment Chart for Sikafloor® Marine Applications

# PACKAGING INFORMATION

Sikafloor® Marine-570 (A)

Container	15.8 kg
Sikafloor® Marine-570 (B)	
Container	4.2 kg

#### BASIS OF PRODUCT DATA


All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

#### **HEALTH AND SAFETY INFORMATION**

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

#### **DISCLAIMER**

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or endusers of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.



Version 04.01 (09 - 2024), en\_DK 012119015704001000 Sika Danmark A/S Hirsemarken 5 3520 Farum Tlf. +45 48 18 85 85 www.sika.dk







