

PRODUCT DATA SHEET

Sikalastic®-1K

One-component cementitious mortar, fibre-reinforced for flexible waterproofing and concrete protection

DESCRIPTION

Sikalastic®-1K is a one-component, crack-bridging, fibre-reinforced mortar, based on cement modified with special alkali-resistant polymers. Sikalastic®-1K is suitable for application by brush or trowel.

USES

- Flexible waterproofing and protection of concrete structures including tanks, basins, pipes etc.
- Waterproofing of bathrooms, showers, terraces, balconies, swimming pools before the application of ceramic tiles bonded with adhesives
- Waterproofing of external wall surfaces to be back-filled in ground
- Inside waterproofing of negative water pressure of walls and floors in basements
- Flexible protection coating for reinforced concrete structures against the effects of freeze-thaw and carbon dioxide attack to improve durability

CHARACTERISTICS / ADVANTAGES

- One-component product, only water needs to be added
- Adjustable consistency, easy to apply by brush or trowel
- Good sag resistance and easy to apply, even on vertical surfaces
- Good crack-bridging ability
- Very good adhesion on many substrates including concrete, cement mortars, stone, masonry
- Can be applied on damp substrates

APPROVALS / CERTIFICATES

- CE-marking and Declaration of Performance as liquid-applied water impermeable product, based on polymer modified cementitious mortars for all external installations and swimming pools beneath ceramic tiling CMO1P according to EN 14891:2012 / AC:2012, based on assessment by notified laboratory and factory production control.
- CE-marking and Declaration of Performance as surface protection product for concrete - coating for ingress protection, moisture control and increasing resistivity according to EN 1504-2:2004, based on certificate of factory production control issued by notified factory production control certification body and type testing.
- Italian Regulation D.M. 174-2004 (Drinking water)

PRODUCT INFORMATION

Composition	Cement modified with alkali resistant polymers, selected aggregates, fine fillers admixtures, additives and fibres.
Packaging	20 kg bags
Appearance / Colour	Light grey
Shelf life	12 months from date of production

Storage conditions Store properly in the original packaging, in cool and dry conditions. Protect from water.

Maximum grain size D_{\max} : ~0,3 mm

TECHNICAL INFORMATION

Tensile adhesion strength $\geq 0,8 \text{ N/mm}^2$ (EN 1542)

Value obtained with a total layer thickness of 3 mm in two layers with 22 % water

Test method **Requirement** (EN 14891)

Initial tensile adhesion strength A.6.2 $\geq 0,5 \text{ N/mm}^2$

Tensile adhesion strength after water contact A.6.3 $\geq 0,5 \text{ N/mm}^2$

Tensile adhesion strength after heat aging A.6.5 $\geq 0,5 \text{ N/mm}^2$

Tensile adhesion strength after freeze-thaw cycles A.6.6 $\geq 0,5 \text{ N/mm}^2$

Tensile adhesion strength after contact with lime water A.6.9 $\geq 0,5 \text{ N/mm}^2$

Tensile adhesion strength after contact with chlorinated water A.6.7 $\geq 0,5 \text{ N/mm}^2$

Values obtained with a total consumption of 3.6 kg/m^2 in two layers with 30 % water

Crack bridging ability $> 0,50 \text{ mm}$ (Class A 3, $+23 \text{ }^\circ\text{C}$)¹ (EN 1062-7)

$\geq 0,75 \text{ mm}$ ($+23 \text{ }^\circ\text{C}$)² (EN 14891 A.8.2)

$\geq 0,75 \text{ mm}$ ($-5 \text{ }^\circ\text{C}$)² (EN 14891 A.8.3)

¹ Value obtained with a total layer thickness of 3 mm in two layers with 22 % water

² Value obtained with a total consumption of 3.6 kg/m^2 in two layers with 30 % water

Reaction to fire Euroclass A2 (EN 13501-1)

Freeze thaw de-icing salt resistance $\geq 0.8 \text{ N/mm}^2$ (EN 13687-1)

Value obtained with a total layer thickness of 3 mm in two layers with 22 % water

Permeability to water vapour Class I (permeable) $S_D < 5 \text{ m}$ (EN ISO 7783-1)

Value obtained with a total layer thickness of 3 mm in two layers with 22 % water

Capillary absorption $\sim 0,02 \text{ kg/m}^2 \cdot \text{h}^{0.5}$ (EN 1062-3)

Value obtained with a total layer thickness of 3 mm in two layers with 22 % water

Water penetration under pressure No penetration after 72h at 5.0 bar¹ (EN 12390-8)²

No penetration after 7 days at 1.5 bar³ (EN 14891 A.7)

¹ Value obtained with a total layer thickness of 3 mm in two layers with 22 % water

² modified

³ Value obtained with a total consumption of 3.6 kg/m^2 in two layers with 30 % water

Water penetration under negative pressure no penetration after 72h at 2.5 bar (UNI 8298/8)

Value obtained with a total layer thickness of 3 mm in two layers with 22% water

Permeability to carbon dioxide $S_D \geq 50 \text{ m}$ (EN 1062-6)

Value obtained with a total layer thickness of 3 mm in two layers with 22 % water

PRODUCT DATA SHEET

Sikalastic®-1K

March 2021, Version 01.01

020701010010000180

APPLICATION INFORMATION

Mixing ratio	Application Method	Water dosage
	By brush	~6,0 litres water per 20 kg bag
	By trowel	~4,4 litres water per 20 kg bag
Fresh mortar density	~1,5 kg/l	
Consumption	This depends on the substrate roughness; as a guide: ~1,2 kg/m ² /mm	
Layer thickness	3 mm with constant thickness, applied in minimum 2 layers. Maximum recommended thickness per layer is 2 mm when applied by trowel and 1 mm when applied by brush	
Ambient air temperature	5 °C min. / 35 °C max.	
Substrate temperature	5 °C min. / 35 °C max.	
Pot Life	~30 min at +20 °C	
Waiting time to overcoating	Sikalastic®-1K must be completely hardened before over-coating or water contact.	
	Guide for waiting times at the following temperatures:	
	+20 °C	+10 °C
Horizontal covering by tiles	~2 days	~7 days
Vertical covering by tiles	~2 days	~3 days
Water emulsion coating	~2 days	~3 days
Immersion in water	~2 days	~7 days
Contact with drinkable water	~15 days	~15 days
	Times will vary due to ambient and substrate humidity.	

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- Sikalastic®-1K shall not be smoothed using a float or trowel.
- Protect from rain for at least 24–48 h after application.
- Avoid direct contact with chlorinated water i.e. in swimming pools, by using suitable protection.
- Avoid application in direct sun light, when rain is imminent or in strong winds.
- Setting time can be influenced by high relative humidity, particularly in closed rooms or basements. The use of adequate ventilation is recommended.
- Before contact with drinking water, ensure the Sikalastic®-1K is completely hardened respecting the suggested waiting times and wash carefully to remove dust, loose material or stagnant water, according to local regulations.
- Sikalastic®-1K is permeable to water vapour and does not form a vapour barrier for resin based systems not permeable to gas.
- If a solvent based paint is to be applied on Sikalastic®-1K, carry out preliminary testing in order to en-

sure the solvents do not attack and damage the waterproofing layer.

- When used in contact with drinking water, ensure Sikalastic®-1K and all associated Sika® products comply with the local regulations for drinking water contact.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Substrates must be structurally sound, clean, dry and free of all contaminants such as dirt, oil, grease, cement laitance, coatings and other surface treatments etc.

Clean surfaces by blast cleaning, high-pressure water-jetting (400 bar), wire-brushing, grinding etc., in order to remove all previous coatings, any traces of grease, rust, release agents, cement laitance and any other material which could reduce adhesion. All dust deposits from this preparation must also be removed i.e. by

vacuum.

Repair concrete substrates, if necessary, with an appropriate cementitious mortar from the SikaTop® or Sika MonoTop® range of repair materials.

The substrate shall be adequately dampened before application. The surface shall not be moist to the touch and shall not be the dark matte (saturated surface dry) appearance.

MIXING

Sikalastic®-1K can be mixed with a low speed (~ 500 r/min) hand drill mixer, adding the right quantity of water according to the respective application. Once a homogeneous mix is obtained, continue mixing for 3–4 min. The mortar must be homogeneous and lump free. Do not add any additional water or other ingredients. Each bag must be entirely mixed, to avoid faulty particle size distribution of aggregates contained in the powder component.

APPLICATION

Special Requirements:

All connections between the substrate and pipe entries, plant and equipment, light switches etc., must be sealed and watertight. Joints in concrete, pipes or anywhere else in the structure must also be sealed and made watertight.

Use coved details at the floor/wall junctions.

Apply Sikalastic®-1K by:

- spatula/roller: Exerting good and even pressure onto the substrate;
- brush: In 2 directions (diagonally opposite / cross-wise);
- mechanical spray: Refer to Sika Technical Service for details

The optimum waterproofing performance is obtained by applying Sikalastic®-1K by trowel in at least 2 layers, to a total thickness of at least 3 mm.

Application by brush must be undertaken with the maximum attention to uniformly covering the whole surface. The maximum recommended thickness for these methods of application is 1 mm per layer. In these situations, the application of min. 2–3 layers is required (subsequent layers must be applied cross-wise).

Wait until the first layer is dry before applying subsequent layers.

The application shall cover the whole surface of the substrate in a uniform thickness.

Sikalastic®-1K cannot be smoothed using float or sponge trowel. It is possible to smooth the surface as soon as the curing of the product is complete by light abrasion techniques.

Sika Danmark A/S

Hirsemarken 5
3520 Farum
Tlf. +45 48 18 85 85
www.sika.dk



PRODUCT DATA SHEET

Sikalastic®-1K
March 2021, Version 01.01
020701010010000180

CLEANING OF EQUIPMENT

Tools should be thoroughly cleaned with water before the material has set. Hardened mortar can only be removed mechanically.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

Sikalastic-1K-en-DK-(03-2021)-1-1.pdf