

PRODUCT DATA SHEET

Sikacryl® Vent 188 N

Pumpable sealant for ventilating ducts

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Chemical base	Acrylic dispersion
Cure mechanism	Evaporation of water
Color	Grey
Density (uncured)	1.4 kg/l
Solid content	72 %
Tack free time (CQP019-1)	25 minutes
Curing speed	24 hours 3 mm ^A
Application temperature	5 – 30 °C
Service temperature	-40 – 70 °C
Movement accommodation capability	± 10 %
Shelf life	12 months ^B

CQP = Corporate Quality Procedure

^A) 23 °C / 50 % r.h.^B) Stored between 10 – 25 °C in sealed, original container. Protect against frost.**DESCRIPTION**

Sikacryl® Vent 188 N is based on 1-component acrylic dispersion which cures through evaporation of water. It is used as a pumpable sealant for general work within the ventilation industry.

PRODUCT BENEFITS

- Can be processed with suitable membrane pump
- Does not crack during drying
- Waterbased - easy workability

AREAS OF APPLICATION

Sikacryl® Vent 188 N is used as a sealant for ventilation ducts, e.g. sleeve couplings, air-conditioning units, fume cupboards etc. Sikacryl® Vent 188 N has good adhesion to galvanized steel, metals, PVC piping, wood, concrete and glass. Sikacryl® Vent 188 N adheres also to humid and cold sheet metal. This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed ensuring adhesion and material compatibility.

PRODUCT DATA SHEET

Sikacryl® Vent 188 N
Version 03.01 (12 - 2023), en_DK
013531000010008000

METHOD OF APPLICATION

Surface preparation

Surfaces must be clean, dry and free from grease, oil, wax and dust. Loose paint, rust and oxide shall be removed before application.

Application

Sikacryl® Vent 188 N is usually applied by hand using corresponding tool or with air driven membrane pump. The sealant shall be pressed against the surface to avoid entrapment of air. Smoothing is performed with suitable tools, i.e. rubber- or steel- trowel directly after application. The bead shall be protected against water (rain) for at least 12 hours after application.

Removal

Tools are cleaned directly after use with water. Cured sealant is removed with acetone or mechanically. Hands and exposed skin have to be washed immediately using Sika® Cleaner-350H cleaning towels or a suitable industrial hand cleaner and water. Do not use solvents on skin.

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheet

PACKAGING INFORMATION

Bucket	15 l
--------	------

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

DISCLAIMER

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

PRODUCT DATA SHEET

Sikacryl® Vent 188 N
Version 03.01 (12 - 2023), en_DK
013531000010008000

