

PRODUCT DATA SHEET

SikaLastomer®-710

Butyl Sealant

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Chemical base	Butyl
Color (CQP001-1)	White, grey, black
Density (uncured)	1.4 kg/l
Application temperature	10 – 35 °C
Skin time (CQP019-1)	10 – 20 minutes ^A
Shrinkage (CQP014-1)	12 %
Service temperature (CQP513-3)	-30 – 80 °C
Shelf life (CQP016-1)	15 months ^B

CQP = Corporate Quality Procedure ^{A)} 23 °C / 50 % r. h.^{B)} stored (unopened) in a dry place between 5 °C and 30 °C. Protect from direct sunlight.**DESCRIPTION**

SikaLastomer®-710 is an butyl based pasty and non-sagging sealant which contains solvents. The curing takes place by physical drying.

This product can be used for the plastic sealing of joints in many industrial sectors.

PRODUCT BENEFITS

- Easy to apply
- Good adhesive spectrum
- Good ageing resistance
- Plastic behavior
- Cures without heat
- Later disassembly possible

AREAS OF APPLICATION

SikaLastomer®-710 is particularly suitable for plastic seals that can be easily disassembled. It is used in the car, bus, truck and caravan industry. SikaLastomer®-710 shows good adhesion with minimal surface preparation on almost every common substrate used in the above-mentioned fields.

This product is suitable for experienced professional users only. Tests under actual processing conditions and with additional materials such as fibers and release agents must be performed to proof material compatibility.

CHEMICAL RESISTANCE

SikaLastomer®-710 is resistant to fresh water, seawater, limewater, aqueous cleaning solutions; weak resistance to fuels, mineral oils, vegetable and animal fatty oils. The above information is offered for general guidance only. In the view of potential chemical or thermal exposure, it is required to conduct a project related testing.

METHOD OF APPLICATION

Surface preparation

Surfaces must be clean, free from dust, grease, oil and water. If adhesion is crucial it has to be verified by tests on original substrates.

Application

Apply the sealant into the joint with a suitable manual or compressed-air gun, taking care to avoid air entrapment. Do not apply at temperatures below 10 °C or above 35 °C.

Tooling and finishing

Joints made with SikaLastomer®-710 are easily tooled with water and soap.

Removal

On non-porous surfaces let sealant dry and remove by dabbing. On porous surfaces cured SikaLastomer®-710 can only be removed mechanically.

Hands and exposed skin have to be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water. Do not use solvents on skin.

Overpainting

SikaLastomer®-710 can only be overpainted with some watery systems. The paint must be tested for compatibility by carrying out preliminary trials. The elasticity of paints is usually lower than that of sealants. This could lead to cracking of the paint in the joint area.

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry. Copies of the following publications are available on request:

- Safety Data Sheets

PACKAGING INFORMATION

Cartridge	310 ml
-----------	--------

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

DISCLAIMER

Any information or suggestions for use concerning Sika’s products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

