

## PRODUCT DATA SHEET

# Sikalastic®-6100 FX

(formerly MSeal 6100FX)

One component elastic and flexible lightweight membrane for waterproofing and concrete protection

### DESCRIPTION

Sikalastic®-6100 FX is a one-component, cement based, elastic and flexible, lightweight and fast curing membrane for waterproofing and protection of concrete structures, masonry and asphalt covered slabs. When mixed with water, Sikalastic®-6100 FX obtains a fluid consistency so that it can be easily hand applied or sprayed. It creates a membrane resistant to positive and negative hydrostatic with high crack bridging characteristics.

Structures waterproofed with Sikalastic®-6100 FX can be filled with water (including potable water) after 72 hours of curing.

Sikalastic®-6100 FX is composed of specially selected cements, lightweight fillers, sand and special polymers in powder form.

### USES

- For interior and exterior application.
- As a waterproof lining for water retaining structures, including drinking water, pipes, basins, etc.
- To provide foundation protection.
- External waterproofing of small roofs and balconies.
- Waterproofing of bathrooms and shower trays.
- Bridge deck waterproofing.
- To protect concrete surfaces from carbonation and chloride attack.
- For areas constantly submerged in water.
- Suitable as a blow hole filler prior to overcoating.

### FEATURES

- One-component product: only needs water to be added.
- High elastic properties: high crack bridging abilities static and dynamic, maintains elasticity in immersion and down to -10 °C. High durability and protection without cracking.
- Low density/Lightweight formulation: Low consumption providing high yield and time saving in application.
- Rapid curing: Allows early service ability. After 2 hours can be applied the second layer. Tanks and reservoirs can be filled after only 3 days of curing. Also after 3 days can be covered with asphalt.
- Waterproof at 2 mm thickness: Resists up to 5 bars of water pressure.
- Excellent adhesion
- Breathable: Water vapour permeable
- High resistance to carbon dioxide diffusion: Protects concrete from rebar corrosion. A 2 mm coating provides anti-carbonation cover equivalent up to 18 cm of concrete.
- Sulphate resistant
- No ammonia smell: Can be applied in closed spaces.
- Reduced efflorescence appearance risk
- UV resistant: can be used as final coating in exterior applications without compromising its mechanical properties.
- Suitable for contact with drinking water: Complies with Directive (EU) 2020/2184 and WRAS approval certificate.
- Compatible with contact with asphalt up to 180 °C.
- 2 mm thickness can be applied in a single layer, by spraying or trowelling.
- High thickness range: possibility to apply 5 mm in one coat on rough substrates (spray).
- Barrier to radon gas (radon gas diffusion length 0.23 mm).
- Classification CM 01-P according to EN 14891 (for use as a waterproofing under cementitious adhesive).

## SUSTAINABILITY

- Specific EPD in accordance with EN 15804+A2 & ISO 14025 / ISO 21930.
- Conformity with LEED v4 MRc 2 – Environmental Product Declarations (Option 1).
- Conformity with LEED v4 MRc 3 – Sourcing of Raw Materials
- Conformity with LEED v4 MRc 4 – Material Ingredients (Option 2)

## CERTIFICATES AND TEST REPORTS

- CE Marking and Declaration of Performance to EN 1504-2 - Surface protection product for concrete - Coating
  - CE Marking and Declaration of Performance to EN 14891 - Liquid applied water impermeable products for use beneath ceramic tiling bonded with adhesives
- Suitable for contact with drinking water (subject to local regulation):
- WRAS approval
  - Directive (EU) 2020/2184 - [RD 3/2023]

## PRODUCT INFORMATION

<b>Composition</b>	Mix of special lightweight cements and selected aggregates with powdered polymers
<b>Packaging</b>	15 kg bags
<b>Appearance and colour</b>	Available in light grey and white colour.
<b>Shelf life</b>	12 months from date of production if stored properly in undamaged and unopened original sealed packaging in dry and cool conditions
<b>Storage conditions</b>	Store properly in undamaged and unopened original packaging in cool and dry conditions, under cover and clear off the ground. Protect from water, moisture and weather inclemencies and do not store at temperatures over +30 °C.

## TECHNICAL INFORMATION

<b>Abrasion resistance</b>	AR1 (50-100 µm)	(BS EN 13892-4)
<b>Resistance to impact</b>	5 Nm (Class I)	(EN ISO 6272-1)
<b>Tensile adhesion strength</b>	Adhesion strength	>1.5 MPa (EN 1542)
	Adhesion strength after thunder shower cycling (10x) with freeze cycling sand de-icing salts (50x)	>1.5 MPa No bubbles, no cracks, no delamination (EN 13687-2) (EN 13687-1)
	Initial tensile adhesion strength	> 0.5 N/mm <sup>2</sup> A.6.2. (EN 14891)
	Tensile adhesion strength after water contact	> 0.5 N/mm <sup>2</sup> A.6.3. (EN 14891)
	Tensile adhesion strength after heat ageing	> 0.5 N/mm <sup>2</sup> A.6.5. (EN 14891)
	Tensile adhesion strength after freeze-thaw cycle	> 0.5 N/mm <sup>2</sup> A.6.6. (EN 14891)
	Tensile adhesion strength after contact with lime water	> 0.5 N/mm <sup>2</sup> A.6.9. (EN 14891)
	Tensile adhesion strength after contact with chlorinated water	> 0.5 N/mm <sup>2</sup> A.6.7. (EN 14891)

<b>Crack bridging ability</b>	Static crack bridging: (EN 1062-7) <ul style="list-style-type: none"> <li>▪ Class A4 (23 °C)</li> <li>▪ Class A3 (-10 °C)</li> <li>▪ Class A4 (after contact with asphalt at 160°C)</li> </ul> Dynamic crack bridging: <ul style="list-style-type: none"> <li>▪ Class B3.1 (23 °C)</li> <li>▪ Class B3.1 (-10 °C)</li> </ul>
<b>Reaction to fire</b>	Class C-s1, d0 (EN 13501-1)
<b>Chemical resistance</b>	No change observed in the product after 175 days of permanent immersion in: <ul style="list-style-type: none"> <li>▪ Synthetic seawater, based on DIN 50905-4</li> <li>▪ Salt mix solution 30 g/l NaCl, NaNO<sub>3</sub>, and Na<sub>2</sub>SO<sub>4</sub>, based on WTA-Guideline</li> <li>▪ KI (potassium iodide) solution (10 g/l)</li> <li>▪ NaSO<sub>4</sub> solution, based on Wittekindt-process</li> <li>▪ Tap water</li> </ul>
<b>Behaviour after artificial weathering</b>	After 2000h in UV chamber was not observed changes in appearance such as cale, blistering or peeling (EN 1062-11)
<b>Permeability to water vapour</b>	Class I (S <sub>D</sub> < 5 m) (EN ISO 7783)
<b>Capillary absorption</b>	<0.1 kg·m <sup>-2</sup> ·h <sup>-0.5</sup> (EN 1062-3)
<b>Water penetration under pressure</b>	Up to 5 bar (2mm thickness) (EN 12390-8)
<b>Water penetration under negative pressure</b>	Up to 2.5 bar (2 mm thickness) (UNI 8298-8)
<b>Permeability to carbon dioxide</b>	S <sub>D</sub> : 104 m (S <sub>D</sub> > 50m) (EN 1062-6)
<b>Permeability to radon</b>	<ul style="list-style-type: none"> <li>▪ Radon diffusion: 1,12 E<sup>-13</sup>·m<sup>2</sup>·s<sup>-1</sup></li> <li>▪ Radon diffusion length: 0.23 mm</li> </ul>

## APPLICATION INFORMATION

<b>Fresh mortar density</b>	~ 1.2 g/cm <sup>3</sup>
<b>Consumption</b>	~ 1.2 Kg/m <sup>2</sup> /mm of mixed product. ~ 0.9 Kg/m <sup>2</sup> /mm of powder product. For a 2 mm thickness application (reccomended minimum thickness) one bag of 15 Kg covers approx. 8.3 m <sup>2</sup> . For bridge deck slabs covered with asphalt (minimum thickness 2.2 mm) consumption should be 2.5 kg/m <sup>2</sup> . Consumption is influenced by the roughness of the substrate. On rough substrates the quantities required will increase significantly. In these cases, to obtain real consumption calculation based on in-situ tests might be required.
<b>Layer thickness</b>	0.5 - 1,5 mm (up to 5 mm for reprofiling) For waterproofing minimum total thickness is 2 mm. For bridge deck waterproofing minimum 2.2 mm.
<b>Material temperature</b>	+5 °C min. / +35 °C max.
<b>Ambient air temperature</b>	+5 °C min. / +35 °C max. Do not apply if the ambient temperature will fall below +5°C during the following 24 hours. Avoid the application during direct sunlight.
<b>Mixing ratio</b>	5.6-6.2 litres of water per 15 kg bag (38-41%)
<b>Substrate temperature</b>	+ 5 °C min. / + 35 °C max. Do not apply on frozen surfaces.

<b>Maturing time</b>	1–2 minutes
<b>Pot Life</b>	~ 45 minutes at 20 °C ambient and substrate temperature. ~ 30 minutes at 30 °C ambient and substrate temperature.
<b>Waiting time</b>	Second coat after 2 - 5 hours. Cover with tiles after 4-8 hours. Exposure to water pressure / mechanical loads after 3 days. In case of waterproofing in enclosed areas with high humidity, the hardening and commissioning times are considerably longer. Curing time may vary according to environmental conditions: temperature, wind and humidity.

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### SUBSTRATE PREPARATION

It can be applied on concrete and mortar substrates. Surfaces must be clean, sound (recommended tensile strength > 1N/mm<sup>2</sup>) free of oil, grease or any other contaminant. Carefully remove all loose particles and dust. All substrate coatings, defective renders, release agents and other previously applied materials that may reduce the adherence of the product should be removed. The substrate must have a certain roughness to allow mechanical adhesion as well as chemical adhesion. Smooth and not very absorbent substrates should be treated mechanically.

In case of active leaks, these must be plugged using a suitable fast setting mortar (i.e. Sika Monotop®-108 Water Plug).

**Concrete, cementitious substrates:** Prepare the surface by grinding, sandblasting, hydrocleaning, wire brushing or any other appropriate method. For the removal of the remaining dust and particles it is recommended to clean the substrate by means of compressed air. Repair any damaged concrete with a suitable Sika Monotop® mortar.

**Masonry:** Prepare the surface by wire brushing or other appropriate mechanical methods. For the removal of the remaining dust and particles it is recommended to clean the substrate by means of compressed air. All mortar joints must be properly cleaned and coated with a suitable mortar.

### MIXING

Sikalastic®-6100 FX should be mixed on site in clean containers.

Pour 5.6 litres of water (maximum 6.2 l for brush applications) into a clean container, then slowly pour in the 15kg of Sikalastic®-6100 FX. Mix with a low-speed drill mixer (400 – 600 rpm) for approximately 3 minutes, until a thick, batter-like consistency is obtained.

Allow the mixture to stand for approximately 1 – 2 minutes to ensure full saturation of the cement. Re-mix, adding a small quantity of water, if required, to restore the consistency.

Do not mix more material than the quantity which can be used in 45 minutes.

For the first coat, additional 0.6 litre of water per bag can be added to the mixture. Do not exceed 6.2 litres water addition per bag.

### APPLICATION

Sikalastic®-6100 FX can be applied by brush, trowel or sprayed with suitable equipment. Roller application is possible, but not recommended.

Always apply the mix to a pre-dampened surface.

Carefully wet the surface until saturation before application of Sikalastic®-6100 FX. High suction substrates require more dampening than dense substrates. However, make sure there is no freestanding water.

**First coat:** Must be applied to the still damp substrate to ensure adhesion. Care must be taken not to spread the material too thinly. First layer as a bonding slurry with approximately 0,5 mm thickness.

If the material does not adhere correctly (without exceeding the pot-life), or if the material begins to drag or “ball”, do not add more water, the substrate must be re-wetted.

Allow at least 2 hours of curing before applying a second coat (this curing time may vary according to environmental conditions: temperature, wind and humidity; can be up to 5 hours).

**Second coat:** Slightly dampen the first coat and remove excess moisture. Apply a second coat perpendicular to the previous coat. Second layer with approximately 1,5 mm thickness. Ensure a total thickness of material of minimum 2 mm.

**Finishing:** The aesthetic finish of the membrane can be improved by applying a damp sponge floated to the surface of the membrane to give a uniform surface.

#### PRODUCT DATA SHEET

Sikalastic®-6100 FX  
October 2024, Version 08.01  
02070100000002049

## CURING TREATMENT

Under hot or excessive drying conditions prevent the product from drying out by spraying lightly with water. Fog-spray after the initial set has taken place for as long as practicable.

In cold, humid or poorly ventilated environments, curing times may be longer. It may be necessary to leave the application for a longer curing period or to introduce forced air movement.

In case of waterproofing in enclosed areas with high humidity, the hardening and commissioning times are considerably longer.

Do not use dehumidifiers during curing process. Do not use film-forming curing agents under any circumstances.

Avoid rain or direct contact with liquid water during curing.

## CLEANING OF EQUIPMENT

Clean all tools and application equipment with clean water immediately after use.

Hardened / cured material can only be removed mechanically.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

## LEGAL NOTES

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

### Sika Danmark A/S

Hirsemarken 5  
3520 Farum  
Tlf. +45 48 18 85 85  
www.sika.dk



### PRODUCT DATA SHEET

Sikalastic®-6100 FX  
October 2024, Version 08.01  
020701000000002049

Sikalastic-6100FX-en-DK-(10-2024)-8-1.pdf