

PRODUCT DATA SHEET

Sikalastic®-618

ONE-COMPONENT, LIQUID APPLIED POLYURETHANE WATERPROOFING MEMBRANE

DESCRIPTION

Sikalastic®-618 is a one-component, cold applied, moisture-triggered polyurethane membrane. It cures to form a seamless and durable waterproofing solution for exposed roof areas and structures.

USES

Sikalastic®-618 may only be used by experienced professionals.

- For roof waterproofing solutions in both new construction and refurbishment projects
- For roofs displaying complex detail areas, even when accessibility is limited
- For cost efficient life cycle extension of failing roofs

CHARACTERISTICS / ADVANTAGES

- Single component - No mixing, easy and ready to use
- Cold applied - requires no heat or flame
- Seamless membrane
- Compatible with Sika® Reemat Premium - easy to detail
- Easily recoated when needed - no stripping required
- Economic – provides a cost efficient life cycle extension of failing roofs
- Vapour permeable - allows substrate to breathe
- Elastic - retains flexibility even at low temperatures
- Good adhesion to most substrates – see table
- Fast curing - Free from rain damage almost immediately on application

APPROVALS / CERTIFICATES

- Liquid applied roof waterproofing kit according to ETAG 005, ETA 13/0456 issued by Technical Assessment Body British Board of Agrément (BBA), Declaration of Performance 18636122 and provided with the CE marking.
- External fire performance according to ENV 1187:
- B_{Roof}(t1) / Broof (t4) on non-combustible substrates
- B_{Roof}(t1) / Broof (t2) over built up roofing system
- British Standard 476 part 3 Ext F.AA rating non-combustible substrates
- Reaction to fire according to EN13501: Euroclass E

PRODUCT INFORMATION

Composition	One-component, moisture-triggered aromatic polyurethane	
Packaging	15 l (~20.7 kg) metal pail	
Colour	White (RAL 9010), grey (RAL 7045), green (RAL 7009), other colours available upon request. Please contact our customer service, for information of which colors are sold in Denmark.	
Shelf life	9 months from date of production	
Storage conditions	The product must be stored properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures >0 °C and <+25 °C. Higher storage temperatures may reduce shelf life of product. Reference shall also be made to the storage recommendations within the safety data sheet.	
Density	~1.38 kg/l (23 °C)	(EN ISO 2811-1)
Solid content by weight	~79 % (+23 °C / 50 % r.h.)	
Solid content by volume	~67 % (+23 °C / 50 % r.h.)	

TECHNICAL INFORMATION

Tensile Strength	Not Reinforced ~ 4.6 N/mm ²	Reinforced ~ 18 N/mm ²	(EN ISO 527-3)
Elongation at Break	Not Reinforced ~150 %	Reinforced ~20 %	(EN ISO 527-3)
External Fire Performance	On non-combustible substrates	B _{Roof} (t1) / B _{Roof} (t4)	(ENV 1187)
	Over built up roofing system	B _{Roof} (t1) / B _{roof} (t2)	
Reaction to Fire	Euroclass E		(EN 13501)
	Ext F.AA rating Non Combustible substrates		(BS 476-3)
Service Temperature	-20 °C min./ +90 °C max.		

SYSTEMS

System Structure

Roof Coating*

Sikalastic®-618 is applied in 1 or 2 coats

Total consumption $\geq 1.0 \text{ l/m}^2 (\geq 1.42 \text{ kg/m}^2)$

Dry film thickness $\geq 0.7 \text{ mm}$

*For partial reinforcement Sikalastic® Fleece-120 or Sikalastic® Flexitape Heavy is applied at areas with high movement, irregular substrate or to bridge cracks, joints and seams on the substrate as well as for details. For primer, please refer to the Substrate Pre-Treatment table below.

Reinforced Roof Waterproofing

Sikalastic®-618 is applied in one coat reinforced with Sika® Reemat Premium and sealed with a further coat of Sikalastic®-618

Layer	Product	Consumption
1. Primer	please refer to substrate pre-treatment	please refer to PDS of the Primer
2. Base coat	Sikalastic®-618	$\geq 1.0 \text{ l/m}^2$ ($\geq 1.42 \text{ kg/m}^2$)
3. Reinforcement	Sika® Reemat Premium	-
4. Top coat	Sikalastic®-618	$\geq 0.75 \text{ l/m}^2$ ($\geq 1.06 \text{ kg/m}^2$)

Note: These figures are theoretical and do not include for any additional material required due to surface porosity, surface profile, variations in level and wastage.

APPLICATION INFORMATION

Ambient Air Temperature +5 °C min. / +40 °C max.

Relative Air Humidity 5 % r.h. min. / 85 % r.h. max.

Substrate Temperature +5 °C min. / +60 °C max.
 $\geq 3 \text{ °C}$ above dew point

Substrate Moisture Content $\leq 4 \%$ pbw moisture content.
Test method: Sika®-Tramex meter
No rising moisture according to ASTM (Polyethylene-sheet).

Substrate Pre-Treatment

Substrate	Primer
Cementitious substrates	Sika® Concrete Primer or Sika® Bonding Primer
Brick and Stone	Sika® Concrete Primer or Sika® Bonding Primer
Ceramic tiles (unglazed), and concrete slaps	Sika® Concrete Primer or Sika® Bonding Primer
Bituminous felt & coating	Sikalastic® Metal Primer
Metals	Sikalastic® Metal Primer
Ferrous or galvanised metals, lead, copper, aluminium, brass or stainless steel	
Wooden substrates	Timber based roof decks require a complete layer of Sikalastic® Carrier. For small exposed timber sections, use Sika® Concrete Primer or Sika® Bonding Primer
Paints	Subject to adhesion and compatibility tests
Existing SikaRoof® MTC System	Sika® Reactivation Primer

For the consumption rates and waiting time / overcoating you should refer to the PDS of the appropriate cleaner and primer. Other substrates must be tested for their compatibility. If in doubt, apply a test area first.

PRODUCT DATA SHEET

Sikalastic®-618

May 2020, Version 02.01

02091520500000013

Pot Life

Sikalastic®-618 is designed for fast drying. High temperatures combined with high air humidity will increase the curing process. Thus, material in opened containers should be applied immediately. In opened containers, the material will form a film after 1 hour approx. (+20 °C / 50 % r.h.)

Waiting Time / Overcoating

Ambient conditions	Minimum waiting time*
+5 °C / 50 % r.h.	18 hours
+10 °C / 50 % r.h.	8 hours
+20 °C / 50 % r.h.	6 hours
+30 °C / 50 % r.h.	4 hours

*After four days the surface must be cleaned and primed with Sika® Reactivation Primer before continuing.

Note: Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.

Applied Product Ready for Use

Ambient conditions	Rain resistant*	Touch dry	Full cure
+5 °C / 50 % r.h.	10 minutes	10 hours	19 hours
+10 °C / 50 % r.h.	10 minutes	6 hours	10 hours
+20 °C / 50 % r.h.	10 minutes	4.5 hours	6 hours
+30 °C / 50 % r.h.	10 minutes	2 hours	4 hours

*Be aware that impact of heavy rain or rain showers can physically damage the still liquid membrane.

Note: Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

The surface must be sound, of sufficient strength, clean, dry and free of dirt, oil, grease and other contamination. Depending on the material the substrate must be primed or mechanically cleaned. Grinding may be necessary to level the surface. Suitable substrates are such as: concrete, bituminous felts and coatings, metal, brickwork, asbestos cement, ceramic tiles, wooden substrates.

For detailed information regarding substrate preparation and primer chart please refer to Method Statement No. 850 915 09.

MIXING

Mixing is not required, however if the product is settled or separated on opening, stir Sikalastic®-618 gently but thoroughly in order to achieve a uniform colour. Stirring gently will minimise air entrainment.

APPLICATION

Prior the application of Sikalastic®-618 the priming coat if used must have cured tack-free. For the Waiting Time / Overcoating please refer to the PDS of the appropriate primer. Damageable areas (handrails, etc) have to be protected with tape or plastic wrapping.

Roof Coating:

Sikalastic®-618 is applied in two coats. Prior to the application of a 2nd coat the indicated waiting time in the table Waiting Time / Overcoating shall be allowed.

Roof coatings may need partial reinforcement over areas of stress or predictable movement eg joints overlaps detailing etc. Use Strips or sections of Sika

Reemat Premium for reasonably sound surfaces –asbestos cement etc. For joints with moderate movement eg Metal Sheeting use Sika Flexitape Heavy incorporating bond-break

Reinforced Roof Waterproofing:

Sikalastic®-618 is applied in combination with Sika Reemat Premium.

1. Apply first coat of approximately 1 l/m² of Sikalastic®-618. Work only so far in advance that the material stays liquid.
2. Roll in the Sikalastic® Reemat Premium. Overlap it a minimum 5 cm and ensure overlaps are sufficiently wet to bond both layers.
3. The roller may require only a little extra material to keep wetted but no further significant material needs to be added at this stage.
4. After the coat is dry enough to walk on, seal the roof area with second coat of Sikalastic®-618 at a minimum 0.75 l/m² per coat.

Please note, always begin with details prior starting with waterproofing the horizontal surface. For details follow step 1-4.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically.

PRODUCT DATA SHEET

Sikalastic®-618

May 2020, Version 02.01

020915205000000013

IMPORTANT CONSIDERATIONS

- Do not apply Sikalastic®-618 on substrates with rising moisture.
- Sikalastic®-618 is not suitable for permanent water immersion.
- On substrates likely to exhibit out-gassing, apply during falling ambient and substrate temperature. If applied during rising temperatures “pin holing” may occur from rising air.
- Do not dilute Sikalastic®-618 with any solvent.
- Do not use Sikalastic®-618 for indoor applications.
- Do not apply close to the air intake vent of a running air conditioning unit.
- Do not apply Sikalastic®-618 directly on Sikalastic® Insulation boards. Instead use Sikalastic® Carrier between Sikalastic® Insulation board and Sikalastic®-618.
- Volatile bituminous materials may stain and or soften below the coating.
- Areas with high movement, irregular substrates, or timber based roof decks require a complete layer of Sikalastic® Carrier.
- Do not apply cementitious products (e.g. tile mortar) directly onto Sikalastic®-618.
- Sikalastic®-618 may exhibit slight chalking at the surface – do not use run off water for live fish tanks, etc.
- Volatile bituminous materials may stain and or soften below the coating.
- Low melting point bituminous materials may need priming – using a darker shade also helps hide any staining from the volatiles.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

Sika Danmark A/S
Hirsemarken 5
3520 Farum
Tlf. +45 48 18 85 85
www.sika.dk



PRODUCT DATA SHEET
Sikalastic®-618
May 2020, Version 02.01
020915205000000013

LEGAL NOTES

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

Sikalastic-618-en-DK-(05-2020)-2-1.pdf