

PRODUCT DATA SHEET

Sikafloor®-1590

Low odour fast curing epoxy primer

DESCRIPTION

Sikafloor®-1590 is a 2-part, low odour, fast curing epoxy resin based primer and scratch coat for flooring applications.

USES

Sikafloor®-1590 may only be used by experienced professionals.

The Product is used as a:

- Primer for concrete substrates, cement screeds and epoxy mortars
- Primer for low to medium absorbent substrates
- Primer for Sika® epoxy and polyurethane flooring systems

FEATURES

- Fast curing
- Good bond strength
- Good penetration
- Low VOC emissions
- Low odour

SUSTAINABILITY

- Contributes towards satisfying Materials and Resources (MR) Credit: Building Product Disclosure and Optimization — Material Ingredients under LEED® v4

CERTIFICATES AND TEST REPORTS

- CE marking and declaration of performance based on EN 13813:2002 Screed material and floor screeds — Screed material — Properties and requirements — Synthetic resin screed material
- CE marking and declaration of performance based on EN 1504-2:2004 Products and systems for the protection and repair of concrete structures — Surface protection systems for concrete — Coating

PRODUCT INFORMATION

Composition	Solvent free epoxy	
Packaging	Container Part A	8.5 kg or 25.5 kg
	Container Part B	1.5 kg or 4.5 kg
	Container Part A + Part B	10 kg or 30 kg ready to mix unit
	Refer to the current price list for available packaging variations.	
Shelf life	12 months from date of production	
Storage conditions	The Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging. Refer to the current Safety Data Sheet for information on safe handling and storage.	

Appearance and colour	Part A	Brownish-transparent, liquid	
	Part B	transparent, liquid	
Density	Part A	~1.49 kg/l	(EN ISO 2811-1)
	Part B	~1.00 kg/l	
	Mixed Product	~1.39 kg/l	
Solid content by mass	~100 %		
Solid content by volume	~100 %		

TECHNICAL INFORMATION

Tensile adhesion strength	> 1.5 N/mm ² (failure in concrete)	(EN 1542)
---------------------------	---	-----------

APPLICATION INFORMATION

Mixing ratio	Part A : Part B (by weight)	85 : 15
--------------	-----------------------------	---------

Sikafloor®-54 Booster

Note: Add between 2 % and 4 % of Sikafloor®-54 Booster, by weight of the mixed resin, to the Product to decrease the waiting times.

Consumption	Application type	Product	Consumption
	Priming	1–2 × Sikafloor®-1590 + max 4 % by weight Sikafloor®-54 Booster	1–2 × 0.35–0.55 kg/m ²
	Scratch coat (surface roughness < 2 mm)	1 pbw Sikafloor®-1590 + 0.5 pbw quartz sand (0.1–0.3 mm) + max 4 % by weight Sikafloor®-54 Booster	1.7 kg/m ² per mm thickness

Material temperature	Minimum	+8 °C
	Maximum	+23 °C

Ambient air temperature	Minimum	+8 °C
	Maximum	+30 °C

Relative air humidity	Maximum	80 % r.h.
-----------------------	---------	-----------

Dew point	Beware of condensation. The substrate and uncured applied product must be at least +3 °C above dew point to reduce the risk of condensation or blooming on the surface of the applied product. Low temperatures and high humidity conditions increase the probability of blooming.
-----------	--

Substrate temperature	Minimum	+8 °C
	Maximum	+23 °C

Substrate moisture content	Substrate	Test method	Moisture content
	Cementitious substrates	Calcium carbide method (CM-method)	≤ 4 %

No rising moisture (ASTM D4263, polyethylene sheet)

Temporary moisture barrier

Note: If the substrate moisture content measured with the CM-method is > 4% by weight, apply a temporary moisture barrier consisting of Sikafloor® EpoCem®.

1. Contact Sika technical services for more information.

Pot Life

Temperature	Without Sika-floor®-54 Booster	With 2 % Sika-floor®-54 Booster	With 4 % Sika-floor®-54 Booster
+8 °C	~90 minutes	~75 minutes	~70 minutes
+10 °C	~90 minutes	~70 minutes	~55 minutes
+15 °C	~50 minutes	~40 minutes	~35 minutes
+23 °C	~30 minutes	~15 minutes	-

Waiting time to overcoating

Before overcoating the Product allow the following waiting times:
WITHOUT SIKAFLOOR®-54 BOOSTER ADDED

Temperature	Minimum without Sika-floor®-54 Booster	Maximum without Sika-floor®-54 Booster
+8 °C	~8 hours	~3 days
+10 °C	~6 hours	~3 days
+15 °C	~5 hours	~48 hours
+23 °C	~3 hours	~24 hours

WITH 2 % SIKAFLOOR®-54 BOOSTER ADDED

Temperature	Minimum with 2 % Sika-floor®-54 Booster	Maximum with 2 % Sika-floor®-54 Booster
+8 °C	~7 hours	~3 days
+10 °C	~5 hours	~3 days
+15 °C	~4 hours	~48 hours
+23 °C	~2 hours	~24 hours

WITH 4 % SIKAFLOOR®-54 BOOSTER ADDED

Temperature	Minimum with 4 % Sika-floor®-54 Booster	Maximum with 4 % Sika-floor®-54 Booster
+8 °C	~6 hours	~3 days
+10 °C	~4 hours	~3 days
+15 °C	~3 hours	~48 hours

Note: Times are approximate and will be affected by changing ambient conditions, particularly temperature and relative humidity.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER INFORMATION

Refer to the following method statements:

- Sika Method Statement — Sikafloor® and Sikagard® evaluation and preparation of surfaces
- Sika Method Statement — Sikafloor® mixing and application

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

EQUIPMENT

MIXING EQUIPMENT

- Electric double paddle mixer (>700 W, 300 to 400 rpm)

APPLICATION EQUIPMENT

- Short pile roller

SUBSTRATE QUALITY

Cementitious substrates must be structurally sound and of sufficient compressive strength (minimum 25 N/mm²) with a minimum tensile strength of 1.5 N/mm².

Substrates must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings, laitance, surface treatments and loose friable material.

PRODUCT DATA SHEET

Sikafloor®-1590

October 2023, Version 04.01

020811020010000126

SUBSTRATE PREPARATION

MECHANICAL SUBSTRATE PREPARATION

IMPORTANT

Exposing blow holes and voids

When mechanically preparing the surface, make sure to fully expose blow holes and voids.

1. Remove weak cementitious substrates.
2. Prepare cementitious substrates mechanically using abrasive blast cleaning or planing / scarifying equipment to remove cement laitance.
3. Before applying thin layer resins, remove high spots by grinding.
4. Use industrial vacuuming equipment to remove all dust, loose and friable material from the application surface before applying the Product.
5. Use products from the Sikafloor®, Sikadur® and Sikagard® range of materials to level the surface or fill cracks, blow holes and voids.

Contact Sika® Technical Services for additional information on products for levelling and repairing defects.

SUBSTRATE PREPARATION OF NON-CEMENTITIOUS SUBSTRATES

For information on substrate preparation of non-cementitious substrates, contact Sika technical services.

TREATMENT OF JOINTS AND CRACKS

Construction joints and existing static surface cracks in substrate require pre-treating before full layer application. Use Sikadur® or Sikafloor® resins.

MIXING

IMPORTANT

Higher amounts of Sikafloor®-54 Booster at higher ambient temperatures

If more than 2 % of Sikafloor®-54 Booster is added at ambient temperatures higher than +15 °C, the exothermic reaction increases and the product will start foaming very quickly.

IMPORTANT

Exothermic reaction

Do not leave the mixed product in its container after the end of the pot life, as the exothermic reaction of the product leads to foaming.

1. At the end of the Product's pot life, fill the container completely with quartz sand to stop the exothermic reaction.

Note: To increase the viscosity of the Product you can add Sika® Extender T.

1. Mix Part A (resin) for ~30 seconds.
2. Add Part B (hardener) to Part A.
3. Mix continuously for 3 minutes, until a uniform mix is achieved.
4. If necessary, gradually add the required amount of Sikafloor®-54 Booster.
5. If additional materials were added, mix for a further 2 minutes until a uniform mix is achieved.
6. To ensure thorough mixing, pour materials into another container and mix again to achieve a smooth and uniform mix.
7. During the final mixing stage, scrape down the sides and bottom of the mixing container with a flat or straight edge trowel at least once to ensure complete mixing.

APPLICATION

IMPORTANT

No application on rising moisture

Do not apply on substrates with rising moisture.

IMPORTANT

Protect from moisture

After application, protect the Product from damp, condensation and direct water contact for at least 24 hours.

IMPORTANT

Temporary heating

If temporary heating is required, do not use gas, oil, paraffin or other fossil fuel heaters. These produce large quantities of both carbon dioxide and water vapour, which may adversely affect the finish.

1. For heating, use only electric powered warm air blower systems.

IMPORTANT

Pin holes

If the Product is applied on porous substrates during rising temperatures, pin holes may form from rising air.

1. Apply the Product during falling temperatures.

PRODUCT DATA SHEET

Sikafloor®-1590

October 2023, Version 04.01

020811020010000126

IMPORTANT

Closing Pin holes

If pin holes are present after the Product has cured blistering may occur in the subsequent layer. Close any pin holes using the following steps.

1. Lightly grind the cured surface.
2. Apply a scratch coat consisting of the Product mixed with ~3 % of Sika® Extender T.

STANDARD PRIMER APPLICATION

1. Pour the mixed Product onto the substrate.
Note: The consumption is specified in Application Information.
2. Apply the Product evenly over the surface with a short pile roller or a squeegee.
3. Back roll the surface in two directions at right angles with a fleece roller.
Note: Maintain a "wet edge" during application to achieve a seamless finish.
4. If broadcasting is required, wait between 15 and 30 minutes, then broadcast the surface with quartz sand. Broadcast lightly at first, then to excess.
5. **IMPORTANT** Confirm waiting or overcoating time is achieved before applying subsequent products. (Refer to the "waiting time to overcoating" section of Application Information) Once the product has hardened sufficiently, remove all loose sand with industrial vacuuming equipment.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

Sika Danmark A/S

Hirsemarken 5
3520 Farum
Tlf. +45 48 18 85 85
www.sika.dk



PRODUCT DATA SHEET

Sikafloor®-1590

October 2023, Version 04.01
020811020010000126

Sikafloor-1590-en-DK-(10-2023)-4-1.pdf